

INTERNATIONAL
STANDARD

ISO
1954

First edition
1999-04-01

Plywood — Tolerances on dimensions

Contreplaqué — Tolérances sur dimensions

STANDARDSISO.COM : Click to view the full PDF of ISO 1954:1999



Reference number
ISO 1954:1999(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 1954 was prepared by Technical Committee ISO/TC 89, *Wood-based panels*, Subcommittee SC 3, *Plywood*.

STANDARDSISO.COM : Click to view the full PDF of ISO 1954:1999

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Plywood — Tolerances on dimensions

1 Scope

This International Standard specifies dimensional tolerances of plywood panels (length, width, thickness) and tolerances for squareness and edge straightness.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 9425:1989, *Wood-based panels — Determination of moisture content*

ISO 9426-1:1989, *Wood-based panels — Determination of dimensions — Part 1: Determination of thickness, width and length.*

3 Moisture content of panels

Moisture content shall be measured in accordance with ISO 9425. Tolerances are fixed with regard to a reference moisture content of (10 ± 2) %.

4 Tolerances on length and width

Length and width shall be measured in accordance with ISO 9426-1.

Tolerances on nominal size: $\pm 3,5$ mm.

5 Tolerances on thickness

Thickness shall be measured in accordance with ISO 9426-1.

Table 1 — Tolerances

Dimensions in millimetres

Nominal thickness (<i>t</i>)	Unsanded panels		Sanded panels	
	Thickness tolerance within one panel	Tolerance on nominal thickness	Thickness tolerance within one panel	Tolerance on nominal thickness
$3 \leq t \leq 12$	1,0	+ (0,8 + 0,03 <i>t</i>)	0,6	+ (0,2 + 0,03 <i>t</i>)
$12 < t \leq 25$	1,5	− (0,4 + 0,03 <i>t</i>)		− (0,4 + 0,03 <i>t</i>)

NOTE Some uses of plywood may require narrower tolerances; see specific standards for board types.

6 Tolerance on straightness of edges

Measurement of the straightness of the edges will be the subject of a future International Standard.

Tolerance: 1 mm/m.

7 Tolerance on squareness

Measurement of squareness will be the subject of a future International Standard.

Tolerance: 1 mm/m.