



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
485 LEXINGTON AVENUE, NEW YORK, N.Y. 10017

AMS 3196B

Superseding AMS 3196A

Issued 7-1-57

Revised 5-1-68

SILICONE RUBBER SPONGE Closed Cell, Firm

SAE Technical Board rules provide that: 'All technical reports, including standards and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents.'

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Sheet, strip, molded shapes, and extrusions.

3. APPLICATION: Primarily for general applications requiring the use of closed cell firm sponge rubber that will be flexible from -75 to +205 C (-103 to +401 F). Compression set may be high at the higher temperatures.

4. TECHNICAL REQUIREMENTS:

4.1 General:

4.1.1 Finish: Unless otherwise specified, the top and bottom surfaces of sheet and strip and the exterior surfaces of molded parts and extrusions (except ends) shall have a natural finish.

4.2 Properties: The product shall conform to the following requirements. Tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable.

4.2.1 As Received:

4.2.1.1 Compression - Deflection, psi 12 - 20

ASTM D1056

Temperature: 20 - 30 C
(68 - 86 F)

4.2.1.2 Density, lb per cu in., max 0.030

4.2.2 Compression Set:

4.2.2.1 Per cent of original deflection, max 60

ASTM D1056

Temperature: 100 C \pm 1
(212 F \pm 1.8)
Time: 22 hr

4.2.2.2 Per cent of original thickness, max 30

4.2.3 Low Temperature Brittleness: Pass

ASTM D736 (See Note 1)

Temperature: -75 C \pm 3
(-103 F \pm 5.4)
Time: 5 hr

Note 1. To be specified only until satisfactory replacement test and values are established.

5. QUALITY: The product shall be uniform in quality and condition, clean, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. TOLERANCES: Unless otherwise specified, the following tolerances shall apply; measurements shall be made in accordance with the issue of ASTM D1056 listed in the latest issue of AMS 2350.