

AEROSPACE MATERIAL SPECIFICATION

SAE AMS3388

REV. D

Issued 1958-08
Revised 1993-10
Reaffirmed 2012-12
Superseding AMS3388C

Hose, Aircraft Fueling, Acrylonitrile Butadiene (NBR) Rubber
Single Wire Braid Reinforced, Chloroprene Covered, Noncollapsing

RATIONALE

AMS3388D has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers a synthetic rubber in the form of a non-rigid, smooth bore, noncollapsing-type hose.

1.2 Application:

This hose has been used typically for fueling aircraft, but usage is not limited to such applications. This hose is not intended for flexible connection between tractor and trailer, to be collapsed for drainage, or for operating pressures higher than 185 psi (1276 kPa).

1.3 Safety-Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The applicable issue of referenced publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3388D>**

2.1 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 380 Testing Rubber Hose
ASTM D 471 Rubber Property - Effect of Liquids

2.2 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-775 Hose, Hose Assemblies; Rubber, Plastic, Fabric, or Metal (Including Tubing); and Fittings, Nozzles, and Strainers, Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material and Fabrication:

3.1.1 Hose: Shall consist of an acrylonitrile butadiene (NBR) rubber inner tube, single corrosion resistant steel wire braided reinforcement, and a chloroprene (CR) rubber cover. In addition to the steel wire reinforcement, one or more textile braids or plies may be incorporated at manufacturer's option.

3.1.1.1 Tube: Shall be fabricated from a compound based on a copolymer of acrylonitrile and butadiene. Thickness of tube shall be not less than 0.078 inch (1.98 mm). The bore shall be smooth and free from pitting and from objectionable cuttings, borings, and cements.

3.1.1.2 Reinforcement: Shall be well, evenly, and firmly braided, and shall be free from dirt, lumps, and irregularities of braid.

3.1.1.3 Cover: Shall be chloroprene (CR) rubber, or other types or blends having equivalent resistance to weathering and petroleum products, and shall be free from pitting.

3.2 Properties:

Hose shall conform to requirements shown in Table 1, 3.2.2, 3.2.3, 3.2.4, and 3.2.5; tests shall be performed on the hose supplied and, except as otherwise specified herein, in accordance with ASTM D 380, insofar as practicable.

TABLE 1 - Aromatic Fuel Resistance

Paragraph	Property	Requirement	Test Method
3.2.1	Aromatic Fuel Resistance: (Immediate Deteriorated Properties)		ASTM Ref. Fuel B (See ASTM D 471) 20 to 30 °C (68 to 86 °F)
3.2.1.1	Volume Change:		22 hours ± 0.2
3.2.1.1.1	Tube	0 to +50%	
3.2.1.1.2	Cover	0 to +100%	

- 3.2.2 Burst Pressure: Hose shall withstand the minimum pressure specified in Table 2 without bursting, leaking, or developing blisters in the cover.

TABLE 2 - Minimum Burst Pressure

Nominal ID Inches	Nominal ID mm	Pressure psi	Pressure kPa
2	50.8	1000	6895
2-1/2	63.5	750	5171
3	76.2	750	5171

- 3.2.3 Change in Length Under Pressure: Hose shall not change in length by more than 7% when subjected to a pressure of 250 psi (1724 kPa).
- 3.2.4 Corrosion: The hose shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and supplier. Discoloration of metal shall not be considered objectionable. Standards for acceptance shall be as agreed upon by purchaser and supplier.
- 3.2.5 Weather Resistance: When specified, hose shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and supplier.

3.3 Quality:

Hose, as received by purchaser, shall be uniform in quality and condition, smooth, and free from foreign materials and from imperfections detrimental to usage of the hose.

3.4 Standard Sizes, Weights, and Tolerances:

Hose shall be furnished in lengths of 50 feet $\pm$ 0.5 (15.2 m $\pm$ 0.15) and to the dimensions and weights shown in Table 3. Lengths from which samples have been cut may be accepted as full lengths if the other technical requirements are met:

TABLE 3A - ID and Weight Tolerances, Inch/Pound Units

Nominal ID Inches	ID Tolerance Inch plus and minus	Weight Without Couplings pounds per foot max
2	1/16	0.6
2-1/2	1/16	1.9
3	1/16	2.3

TABLE 3B - ID and Weight Tolerances, SI Units

Nominal ID mm	ID Tolerance Millimeters plus and minus	Weight Without Couplings kg/m, max
50.8	1.6	2.4
63.5	1.6	2.8
76.2	1.6	3.4

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The manufacturer of hose shall supply all samples and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the hose conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for aromatic fuel resistance (3.2.1), burst pressure (3.2.2), and change in length under pressure (3.2.3) are acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of hose by the manufacturer, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient hose shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all hose of the same size produced in a single production run, from the same batches of raw materials, under the same fixed conditions, and presented for manufacturer's inspection at one time.

4.3.1.2 When a statistical sampling plan has been agreed upon by purchaser and manufacturer, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and supplier.

4.4 Approval:

4.4.1 Sample hose shall be approved by purchaser before hose for production use is supplied, unless such approval be waived by purchaser. Results of tests on production hose shall be essentially equivalent to those on the approved sample.

4.4.2 Manufacturer shall use ingredients, manufacturing procedures, processes, and methods of inspection on production hose which are essentially the same as those used on the approved sample. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample hose. Production hose made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports:

The supplier of hose shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the hose conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 3388D, manufacturer's material designation, size, and quantity.