

INTERLEAF CARRIER MATERIAL, COMPOSITE TAPE
Paper, 0.004 in. (0.10 mm), Perforated

1. SCOPE:

1.1 Form: This specification covers one type of paper in the form of perforated tape of the width specified herein.

2. APPLICABLE DOCUMENTS: See AMS 3898.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3898.

3.2 Material: The carrier shall be a paper which has been coated with a silicone release agent, slit to the width specified, and perforated for sprocket alignment as shown in Fig. 1 of AMS 3898.

3.2.1 Thickness: Shall be 0.0040 in. \pm 0.0005 (0.102 mm \pm 0.012).

3.2.2 Width: Shall be 4.000 in. (101.60 mm).

3.3 Properties: Shall be as follows:

3.3.1 Tensile Strength, min 25 lb per in. of width
(4.40 kN/m of width)

3.3.2 Tear Strength, min 2.8 oz
(780 mN)

4. QUALITY ASSURANCE PROVISIONS: See AMS 3898.

5. PREPARATION FOR DELIVERY: See AMS 3898.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.