



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 4008H

Issued NOV 1941
Revised SEP 1994

Superseding AMS 4008G

Submitted for recognition as an American National Standard

ALUMINUM ALLOY, SHEET AND PLATE
1.25Mn - 0.12Cu (3003-H14)
Strain Hardened

UNS A93003

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application:

These products have been used typically for parts requiring moderately severe forming or spinning, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2202	Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate
MAM 2202	Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate
AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units
AMS 2811	Identification, Aluminum and Magnesium Alloy Wrought Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 4008H

SAE

AMS 4008H

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Manganese	1.0	1.5
Copper	0.05	0.20
Iron	--	0.7
Silicon	--	0.6
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Strain hardened.

3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as specified in Table 2.

AMS 4008H

SAE

AMS 4008H

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi, min	Elongation in 2 Inches or 4D %, min
0.009 to 0.012, incl	20.0 to 26.0	17.0	1
Over 0.012 to 0.019, incl	20.0 to 26.0	17.0	2
Over 0.019 to 0.031, incl	20.0 to 26.0	17.0	3
Over 0.031 to 0.050, incl	20.0 to 26.0	17.0	4
Over 0.050 to 0.113, incl	20.0 to 26.0	17.0	5
Over 0.113 to 0.161, incl	20.0 to 26.0	17.0	6
Over 0.161 to 0.249, incl	20.0 to 26.0	17.0	7
Over 0.249 to 0.499, incl	20.0 to 26.0	17.0	8
Over 0.499 to 1.000, incl	20.0 to 26.0	17.0	10

TABLE 2B - Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
0.23 to 0.30, incl	138 to 179	117	1
Over 0.30 to 0.48, incl	138 to 179	117	2
Over 0.48 to 0.79, incl	138 to 179	117	3
Over 0.79 to 1.27, incl	138 to 179	117	4
Over 1.27 to 2.87, incl	138 to 179	117	5
Over 2.87 to 4.09, incl	138 to 179	117	6
Over 4.09 to 6.32, incl	138 to 179	117	7
Over 6.32 to 12.67, incl	138 to 179	117	8
Over 12.67 to 25.40, incl	138 to 179	117	10

- 3.3.2 Bending: Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.009 to 0.113, incl	0.23 to 2.87, incl	0
Over 0.113 to 0.249, incl	Over 2.87 to 6.32, incl	2

AMS 4008H

SAE

AMS 4008H

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.3.1), and

(R) tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each lot.

4.2.2 Periodic Tests: Bending (3.3.2) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

(R)

Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

(R)

The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and showing the results of tests on each lot to determine conformance to the tensile properties and when performed, to the periodic test requirements. This report shall include the purchase order number, lot number, AMS 4008H, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

(R)

Shall be in accordance with AMS 2811.

5.2 Packaging: