

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 4575D

Issued 11-1-49
Revised 10-1-86

Superseding AMS 4575C

NICKEL-COPPER ALLOY TUBING, BRAZED, CORROSION RESISTANT
67Ni - 31Cu
Annealed

UNS N04400

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant nickel-copper alloy in the form of copper-furnace-brazed tubing.

1.2 Application: Primarily for fluid lines, such as primer and fuel lines, requiring corrosion resistance with relatively-high strength.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2263 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
- MAM 2263 - Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
- AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASM E8 - Tension Testing of Metallic Materials

ASTM E76 - Chemical Analysis of Nickel-Copper Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

- 2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E76 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Nickel + Cobalt	63.0	--
Copper	28.0	34.0
Iron	--	2.5
Manganese	--	2.0
Cobalt (3.1.1)	--	1.0
Silicon	--	0.5
Carbon	--	0.3
Sulfur	--	0.024

- 3.1.1 Determination not required for routine acceptance.

- 3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

- 3.2 Condition: Cold drawn after brazing and annealed.

- 3.3 Properties: Tubing shall conform to the following requirements:

- 3.3.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, max	85,000 psi (585 MPa)
Elongation in 2 in. (50 mm) or 4D, min	32%

- 3.3.2 Flareability: Tubing shall withstand flaring, without formation of cracks or other visible defects, by being forced, at room temperature, axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg included angle to produce a flare having a permanent expanded OD not less than 1.25 times the original nominal OD.

- 3.3.3 Pressure Test: Tubing shall show no bulges, leaks, pinholes, cracks, or other defects when subjected to an internal hydrostatic pressure (P), calculated from the following equation:

$$P = \frac{2St}{D}$$

where, P = Test pressure
S = 17,500 psi (120 MPa)
t = Minimum wall thickness
D = Nominal OD

- 3.4 Quality: Tubing, as received by purchaser, shall be uniform in quality and condition, sound, smooth, and free from foreign materials and from imperfections detrimental to usage of the tubing.

- 3.5 Tolerances: Shall conform to all applicable requirements of AMS 2263 or MAM 2263.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for flarability (3.3.2) and pressure test (3.3.3) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling : Shall be in accordance with AMS 2371 and the following:

- 4.3.1 Specimens for flarability test shall be full tubes or sections cut from tubes. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded.

4.4 Reports:

- 4.4.1 The vendor of tubing shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties of each lot and stating that the tubing conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 4575D, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4575D, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification and shall include in the report either a statement that the tubing conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows:

- 5.1.1 Straight Tubes 0.029 In. (0.75 mm) and Over in Wall Thickness and 0.500 In. (12.50 mm) and Over in OD, Minor Axis, or Least Width of Flat Surface: Shall be marked in a row of characters recurring at intervals not greater than 3 ft (900 mm) with AMS 4575D, manufacturer's identification, and nominal wall thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the tubing or its performance and shall be sufficiently stable to withstand normal handling.
- 5.1.2 Straight Tubes Under 0.029 In. (0.75 mm) in Wall Thickness or Under 0.500 In. (12.50 mm) in OD, Minor Axis, or Least Width of Flat Surface: Shall be securely bundled and identified by a durable tag marked with the information of 5.1.1 and the nominal OD and attached to each bundle or shall be boxed and the box marked with the same information.
- 5.1.3 Coiled Tubing: Shall be securely bundled and identified by a durable tag marked with the purchase order number, AMS4575D, heat number, nominal OD and wall thickness, and manufacturer's identification and attached to each coil or shall be boxed and the box marked with the same information.