



AEROSPACE MATERIAL SPECIFICATION

AMS5364™**REV. D**

Issued	1977-07
Revised	2018-08
Reaffirmed	2023-11

Superseding AMS5364C

Steel, Corrosion and Heat-Resistant, Investment Castings
19.5Cr - 10.5Ni - 0.65Cb (Nb) (CF-8C)
Solution Heat Treated
(Composition similar to UNS J92710)

RATIONALE

AMS5364D revises chemical analysis standards (3.1), updates the default NDT acceptance requirement (3.7.4.1), prohibits unauthorized exceptions (3.8), updates Reports (4.5.5), and results from a Five-Year Review and update of this specification.

AMS5364D has been reaffirmed to comply with the SAE Five-Year Review policy.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant steel in the form of investment castings.

1.2 Application

These castings have been used typically for welded structural parts, such as exhaust couplings and fittings, and for parts requiring oxidation resistance up to 1500 °F (816 °C) but useful at higher temperature only when stresses are low, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the reference document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5364D/>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2175	Castings, Classification and Inspection of
AMS2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS2360	Room Temperature Tensile Properties of Castings
AMS2694	In-Process Welding of Castings
AMS2700	Passivation of Corrosion Resistant Steels
AMS2750	Pyrometry
AMS2804	Identification, Castings
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A262	Detecting Susceptibility of Intergranular Attack in Austenitic Stainless Steels
ASTM A751	Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E18	Rockwell Hardness of Metallic Materials
ASTM E1417/E1417M	Liquid Penetrant Testing
ASTM E1742/E1742M	Radiographic Examination

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM A751, by spectrochemical methods, or by other analytical methods acceptable to purchaser (see 8.2.1 and 8.2.2).

Table 1 - Composition

Element	Min	Max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.50
Phosphorus	--	0.04
Sulfur	--	0.03
Chromium	18.00	21.00
Nickel	9.00	12.00
Columbium (Niobium)	8xC	1.00
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Producer may test for any element not otherwise listed in Table 1 and include this analysis in the report of 4.5. Limits of acceptability may be specified by purchaser (see 8.2.3).

3.1.2 Check Analysis

Composition variations shall meet the requirements of AMS2248.

3.2 Melting Practice

Castings and specimens shall be poured at casting producer's facility either from a melt (see 8.2.4) of a master heat, or directly from a master heat (see 3.4.2 and 8.2.5).

3.2.1 Revert (gates, sprues, risers, and rejected castings) may be used only in the preparation of master heats; revert shall not be remelted directly without refining for pouring of castings. Melting of revert creates a new master heat.

3.2.2 Portions of two or more qualified master heats (see 3.4.2) may be melted together and poured into castings using a procedure authorized by purchaser (see 8.2.6).

3.2.3 If melts (see 8.2.4) are modified by replenishment (see 8.2.7), producer shall have a written procedure acceptable to purchaser which defines the controls, test, and traceability criteria for both castings and separately-cast specimens. Control factors of 4.4.2.2 shall apply.

3.3 Condition

Castings shall be delivered in the solution heat treated condition.

3.4 Test Specimens

Specimens shall be either separately-cast, integrally-cast (see 8.2.8), or machined from a casting, and shall conform to 3.2.

3.4.1 If specimens are separately-cast, producer shall have a written procedure acceptable to purchaser. Control factors of 4.4.2.2 shall apply.

3.4.2 Each master heat shall be qualified by evaluation of chemical and tensile specimens.

3.4.2.1 If replenishments are made at remelt as in 3.2.3, frequency of sampling and testing used by the producer for qualification to 3.4.2 shall be acceptable to purchaser.

3.4.2.2 Tensile tests of 3.4.2 are not required if these tests are conducted using integrally-cast specimens (4.3.3.2) or specimens machined-from-casting (4.3.3.3).

3.4.3 Chemical Analysis Specimens

Shall be of any convenient size and shape.

3.4.4 Tensile Specimens

Shall be of standard proportions in accordance with ASTM E8/E8M (see 8.3) with 0.250-inch (6.35-mm) diameter at the reduced parallel gage section.

3.4.4.1 Separately-cast and integrally-cast specimens may be either cast to size, and/or cast oversize and subsequently machined to 0.250-inch (6.35-mm) diameter.

3.4.4.2 When integrally-cast specimens and/or specimens machined-from-casting are specified, specimen size and location shall be agreed upon by purchaser and producer (see 8.2.9 and 8.5).

3.5 Heat Treatment

Castings and representative specimens shall be heat treated as follows. Pyrometry shall be in accordance with AMS2750.

3.5.1 Castings and Specimens

3.5.1.1 Solution Heat Treatment

Heat to 1950 °F ± 50 °F (1066 °C ± 28 °C), hold at heat for not less than 1 hour per inch (25 mm) of maximum section thickness but in no case less than 30 minutes, and rapid cool in air, oil, water, or argon.

3.5.2 Tensile specimens used for master heat qualification may be heat treated separately from castings.

3.6 Properties

Conformance shall be based upon testing of separately-cast specimens unless purchaser specifies integrally-cast specimens or specimens machined-from-casting. Properties for integrally-cast specimens and specimens machined-from-casting shall be as specified by purchaser (see 8.5).

3.6.1 Room Temperature Tensile Properties

Shall be as specified in 3.6.1.1, determined in accordance with ASTM E8/E8M (see 8.3). Properties other than those listed may be defined as specified in AMS2360.

3.6.1.1 Separately-Cast Specimens

Shall be as shown in Table 2.

Table 2 - Minimum tensile properties

Property	Value
Tensile Strength	70 ksi (483 MPa)
Yield Strength at 0.2% Offset	30.0 ksi (207 MPa)
Elongation in 4D	30%

3.6.2 Hardness

Castings and representative specimens, heat treated to the condition of 3.3, shall have a hardness not higher than 88 HRB, determined in accordance with ASTM E18.

3.6.3 Susceptibility to Intergranular Attack

Castings or representative specimens, after sensitizing, shall pass the intergranular corrosion test performed in accordance with ASTM A262, Practice E.

3.7 Quality

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings. Castings shall be free of cracks, laps, hot tears, and cold shuts, and free of scale and other process-induced surface contamination which would obscure defects.

3.7.1.1 Unless otherwise specified, castings shall be sufficiently cleaned such that, after passivation by purchaser, the castings shall meet the corrosion test requirement of AMS2700.

3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of each casting part number until foundry manufacturing controls in accordance with 4.4.2 have been established. Additional radiography shall be conducted in accordance with the frequency of inspection specified by purchaser, or as necessary to ensure continued maintenance of internal quality.

3.7.2.1 Radiographic inspection shall be conducted in accordance with ASTM E1742/E1742M or other method specified by purchaser.

3.7.3 When specified, additional nondestructive testing shall be performed as follows:

3.7.3.1 Fluorescent penetrant inspection in accordance with ASTM E1417/E1417M or other method specified by purchaser.

3.7.4 Acceptance standards for radiographic, fluorescent penetrant, visual, and other inspection methods shall be as agreed upon by purchaser and producer (see 8.2.9). AMS2175 may be used to specify acceptance standards (casting grade) and frequency of inspection (casting class).

3.7.4.1 When acceptance standards are not specified, the following applies: Castings shall meet Grade C of AMS2175 and radiographic indications of gas holes, sand spots, and inclusions shall be cause for rejection when closer to the edge than twice their maximum dimension.

3.7.5 Castings shall not be peened, plugged, impregnated, or welded unless authorized by purchaser.

3.7.5.1 When authorized by purchaser, welding in accordance with AMS2694 or other welding program acceptable to purchaser may be used.

3.8 Any exceptions shall be authorized by purchaser and reported as in 4.5.5.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of castings shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.6.1), and the applicable requirements of quality (3.7) are acceptance tests and shall be performed as specified in 4.3.

4.2.2 Periodic Tests

Hardness (3.6.2), susceptibility to intergranular attack (3.6.3), corrosion resistance (3.7.1.1), and radiographic soundness (3.7.2) are periodic tests and shall be performed at a frequency selected by the producer unless a frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests

All technical requirements are preproduction tests and shall be performed on sample castings (4.3.2), when a change in control factors occurs (4.4.2.2), and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

The minimum testing performed by producer shall be in accordance with the following:

4.3.1 One chemical analysis specimen or a casting from each master heat shall be tested for conformance with Table 1; if 3.4.2.1 applies, test frequency shall be acceptable to purchaser.

4.3.2 One preproduction casting in accordance with 4.4 shall be tested to requirements of the casting drawing and to all technical requirements.

4.3.2.1 Dimensional inspection sample quantity shall be as specified by purchaser.

- 4.3.3 Tensile property tests shall be conducted to determine conformance with 3.6.1. Sampling and test frequency is dependent upon the type and origin of specimen specified by purchaser (see 3.4.4 and 3.6) or selected by producer (see 4.3.3.4). When 3.4.2.1 applies, specimen source and test frequency shall be acceptable to purchaser.
- 4.3.3.1 For separately-cast specimens in the solution heat treated condition, one specimen from each master heat shall be tested for conformance to 3.6.1.
- 4.3.3.2 For integrally-cast specimens in the solution heat treated condition, two specimens from each lot (see 8.2.10) shall be randomly selected and tested for conformance with properties specified by purchaser (see 8.5).
- 4.3.3.3 For specimens machined-from-casting, one casting shall be randomly selected from each lot and tested in the solution heat treated condition at each location shown on the engineering drawing to 3.6.1 for conformance with properties specified by purchaser (see 8.5).
- 4.3.3.3.1 When size and location of specimens are not shown, two specimens shall be tested, one from the thickest section and one from the thinnest section. Once established under 4.4.2.2, test locations may be changed only as agreed upon by purchaser and producer.
- 4.3.3.4 When acceptable to purchaser, specimens machined-from-casting may be used in lieu of both separately-cast and integrally-cast specimens, and integrally-cast specimens may be used in lieu of separately-cast specimens. In each case, the resultant properties must conform to requirements specified by purchaser (see 8.5).
- 4.3.3.4.1 When specimens are selected for test as in 4.3.3.4 from an origin other than that specified by purchaser, producer shall include in the report of 4.5 a description of the source of the specimen that was tested.
- 4.3.3.5 When casting size, section thickness, gating method, or other factors do not permit conformance with 4.3.3.2 or 4.3.3.3, sampling and testing shall be agreed upon by purchaser and producer.
- 4.3.4 Castings shall be inspected in accordance with 3.7 to the methods, frequency, and acceptance standards specified by purchaser.
- 4.4 Approval
- 4.4.1 Sample casting(s) from new or reworked master patterns produced under the casting procedure of 4.4.2 shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
- 4.4.2 For each casting part number, producer shall establish parameters for process control factors that will consistently produce castings and test specimens meeting the requirements of the casting drawing and this specification. These parameters shall constitute the approved casting procedure and shall be used for production of subsequent castings and test specimens. If necessary to make any change to these parameters, producer shall submit a statement of the proposed change for purchaser reapproval. When requested, producer shall also submit test specimens, sample castings, or both to purchaser for reapproval.
- 4.4.2.1 Production castings produced prior to receipt of purchaser's approval shall be at producer's risk.
- 4.4.2.2 Control factors for producing castings and separately-cast specimens include, but are not limited to, the following factors. Suppliers procedures shall identify tolerances, ranges, and/or control limits, as applicable. Control factors for separately-cast specimens must generally represent, but need not be identical to, those factors used for castings (see 3.2.3 and 3.4.1):

Composition of ceramic cores, if used

Arrangement and number of patterns in the mold (including integrally-cast specimens, if applicable)

Size, shape, and location of gates and risers

Mold refractory formulation

Grain refinement methods, if applicable

Mold back-up material (weight, thickness, or number of dips)

Type of furnace, atmosphere, and charge for melting

Mold preheat and metal pouring temperatures

Fluxing or deoxidation procedure
Replenishment procedure, if applicable
Time molten metal is in furnace
Solidification and cooling procedures
Cleaning operations (mechanical and chemical)
Heat treatment
Straightening
Final inspection methods
Location of specimens machined from a casting, if applicable

4.4.2.2.1 Any of the control factors for which parameters are considered proprietary by the producer may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

4.4.2.2.1.1 Unless otherwise agreed upon by purchaser and producer, purchaser shall be entitled to review proprietary control factor details and coding at producer's facility.

4.5 Reports

The producer of castings shall furnish with each shipment a certification document declaring that castings have been processed, tested, and inspected as specified and that the results of the inspections and tests conform to requirements.

4.5.1 Unless otherwise specified, producer shall furnish report(s) showing the results of tests and inspections conducted in accordance with 4.2 and 4.3.

4.5.1.1 Chemical analysis determinations, property test data, and the results of any retests conducted shall be expressed numerically to reflect actual quantitative test values.

4.5.1.2 Hardness test readings may be expressed as single values or as a range of values exhibited by results obtained from the sample size.

4.5.1.3 Inspection and preproduction results shall be reported at the frequency specified by, and in a format acceptable to purchaser.

4.5.1.4 Nonconformances shall be documented and approved by purchaser in accordance with purchaser's material review requirements.

4.5.2 The statement of conformity and report(s) shall include or be traceable to the purchase order number, master heat identification, heat treat/lot number, AMS5364D, part number, quantity, and when required (see 5.1.2) the list of individual serial numbers or serial number range.

4.5.2.1 If 4.3.3.4.1 applies, the mechanical property test report shall denote the source of the specimens that were tested.

4.5.3 Test reports for acceptance testing of 4.2 shall be as follows:

4.5.3.1 For Each Master Heat

Composition (see 4.3.1)
Tensile properties (see 4.3.3.1)

4.5.3.2 For Each Lot

Inspection results (see 4.3.4)
Tensile properties, when specified (see 4.3.3.2 and 4.3.3.3)

4.5.4 The producer shall retain records of processing and inspection in accordance with purchaser requirements.

4.5.5 When castings produced to this specification have exceptions authorized by purchaser taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS5364D(EXC) because of the following exceptions." and the specific exceptions shall be listed.

4.6 Resampling and Retesting

If results of a valid test fail to meet specified requirements, two additional specimens in accordance with 4.3 from the same master heat, modified melt (see 3.2.3), or lot, as applicable, shall be tested for each nonconforming characteristic. Results of each additional test, and the average of the results of all tests (original and retests) shall meet specified requirements; otherwise, the master heat or lot shall be rejected. Results of all tests shall be reported.

4.6.1 A test may be declared invalid if failure is due to specimen mispreparation, test equipment malfunction, improper test procedure, or the presence of random process defects such as inclusions or gas holes in a tensile specimen.

5. PREPARATION FOR DELIVERY

5.1 Identification

Unless otherwise specified by purchaser, individual castings shall be identified in accordance with AMS2804.

5.1.1 Traceability

Individual castings shall be traceable to their conditions of manufacture and inspection up to and including the point of acceptance by purchaser.

5.1.2 Serialization

When specified (see 4.5.2 and 8.5) each casting shall be serialized with a unique non-repeating serial number.

5.2 Packaging

Castings shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the castings to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A producer shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Castings not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES

8.1 Revision Indicator

A change bar (|) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this document. An (R) symbol to the left of the document title indicates a complete revision of the document, including technical revision. Change bars and (R) are not used in original publications, nor in documents that contain editorial changes only.