



AEROSPACE MATERIAL SPECIFICATION	AMS5925™	REV. C
	Issued 1999-05 Reaffirmed 2012-04 Revised 2023-09	
Superseding AMS5925B		
Steel, Corrosion-Resistant, Bars, Wire, Forgings, and Forging Stock 15.5Cr - 1.8Mo - 0.20N (0.37 - 0.45C) Electroslag Remelted (Composition similar to UNS S42025)		

RATIONALE

AMS5925C is the result of a Five-Year Review and update of the specification. The revision updates the Title to match the Scope, prohibits unauthorized exceptions (see 3.7, 4.4.4, and 8.6), adds composition reporting (see 3.1.1), updates finish requirements (see 3.3.1.2), prohibits bar from plate (see 3.3.1.3), revises micro-inclusion requirements (see 3.4.1.2), updates decarburization testing requirements (see 3.4.2.4), removes tolerance on quench (see 3.4.3), adds UT testing option (see 3.5.1 and 4.2.1), updates quality requirements (see 3.5.2 and 8.7), and adds option for additional forging stock requirements (see 4.4.3 and 8.8).

1. SCOPE

1.1 Form

This specification covers a premium aircraft-quality, corrosion-resistant steel in the form of bars, wire, forgings, and forging stock.

1.2 Application

These products have been used typically for anti-friction bearing components requiring resistance to both corrosion and wear, with hardness not lower than 58 HRC after hardening and tempering, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5925C/>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2241	Tolerances, Corrosion- and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS2248	Chemical Check Analysis Limits, Corrosion- and Heat-Resistant Steels and Alloys, Maraging and Other Highly Alloyed Steels, and Iron Alloys
AMS2300	Steel Cleanliness, Premium Aircraft-Quality, Magnetic Particle Inspection Procedure
AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2806	Identification Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels, and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AMSSTD2154	Inspection, Ultrasonic, Wrought Metals, Process for
AS1182	Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel, Bars and Mechanical Tubing
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A370	Mechanical Testing of Steel Products
ASTM A751	Chemical Analysis of Steel Products
ASTM A604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E45	Determining the Inclusion Content of Steel
ASTM E112	Determining Average Grain Size
ASTM E140	Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751, or by other analytical methods acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	0.37	0.45
Manganese	--	0.60
Silicon	--	0.60
Phosphorus	--	0.020
Sulfur	--	0.005
Chromium	15.00	16.50
Molybdenum	1.50	1.90
Vanadium	0.20	0.40
Nitrogen	0.16	0.25
Nickel	--	0.30

3.1.1 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Melting Practice

Steel shall be multiple melted using the electroslag remelt practice in the final melting cycle.

3.3 Condition

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A370:

3.3.1 Bars

Either hot or cold worked, annealed, having hardness not higher than 255 HB, or equivalent (see 8.2).

3.3.1.1 Bars 2.750 inches (69.85 mm) and under in nominal diameter or least distance between parallel sides and all hexagons shall be cold finished.

3.3.1.2 Bars, other than hexagons, over 2.750 inches (69.85 mm) in nominal diameter or least distance between parallel sides shall be either hot finished or cold finished.

3.3.1.3 Bars shall not be cut from plate (see 4.4.2).

3.3.2 Wire

Annealed and cold finished, having tensile strength not higher than 130 ksi (896 MPa).

3.3.3 Forgings

As ordered.

3.3.4 Forging Stock

As ordered by the forging manufacturer.

3.4 Properties

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A370:

3.4.1 Bars, Wire and Forgings

3.4.1.1 Macrostructure

Visual examination of transverse sections from bars, wire, billets, and forging stock etched in hot hydrochloric acid in accordance with ASTM A604 shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections for product 36 square inches (232 cm²) and under in nominal cross-sectional area shall be no worse than the macrographs of ASTM A604 shown in Table 2.

Table 2 - Macrostructure limits

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	B
4	Ring Pattern	B

Limits for larger sizes shall be agreed upon by the purchaser and producer.

3.4.1.2 Micro-Inclusion Rating

No specimens shall exceed the limits of Table 3, determined in accordance with ASTM E45, Method D.

Table 3 - Micro-inclusion rating limits

	A		B		C		D	
	Thin	Heavy	Thin	Heavy	Thin	Heavy	Thin	Heavy
Worst Field Severity	1.5	1.0	1.5	1.0	1.0	1.0	1.5	1.0
Worst Field Frequency, Maximum	a	1	a	1	a	1	3	1
Total Rateable Fields, Frequency, Maximum (c)	b	1	b	1	b	1	c	1

a Combined A+B+C; not more 3 fields

b Combined A+B+C; not more 8 fields

c A+B+C+D; not more 100 fields

3.4.1.2.1 A ratable field is defined as one which has a type A, B, C, or D inclusion rating of at least No. 1.0 thin or heavy in accordance with ASTM E45.

3.4.1.3 Microstructure

The product shall be free of carbide network. For the products of sections between 0.15 square inches and 12.4 square inches (1 cm² and 80 cm²), the maximum carbide size allowed is: 0.0014 inch (35 μm) for isolated carbides, 0.0010 inch (25 μm) for grouped carbides (distance between carbides <0.0020 inch [<50 μm]). The examination shall be carried out at mid-radius (or equivalent) on a surface that is parallel to the grain flow.

3.4.1.4 Average Grain Size

Shall be ASTM No. 6 or finer, determined in accordance with ASTM E112.

3.4.2 Decarburization and Denitridation

- 3.4.2.1 Bars and wire ordered ground, turned, or polished shall be free from decarburization and/or denitridation on the ground, turned, or polished surfaces.
- 3.4.2.2 Allowable decarburization and/or denitridation of bars, wire, and billets ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by the purchaser and producer.
- 3.4.2.3 Decarburization and/or denitridation of bars and wire, to which 3.4.2.1 or 3.4.2.2 is not applicable, shall be not greater than shown in Table 4.

Table 4A - Maximum decarburization/denitridation, inch/pound units

Nominal Diameter or Distance Between Parallel Sides Inches	Total Depth of Decarburization/Denitridation Inches
Up to 0.500, incl	0.015
Over 0.500 to 1.000, incl	0.020
Over 1.000 to 1.500, incl	0.025
Over 1.500 to 2.000, incl	0.030
Over 2.000 to 2.500, incl	0.035
Over 2.500 to 3.000, incl	0.040
Over 3.000 to 4.000, incl	0.045

Table 4B - Maximum decarburization/denitridation, SI units

Nominal Diameter or Distance Between Parallel Sides Millimeters	Total Depth of Decarburization/Denitridation Millimeters
Up to 12.70, incl	0.38
Over 12.70 to 25.40, incl	0.51
Over 25.40 to 38.10, incl	0.64
Over 38.10 to 50.80, incl	0.76
Over 50.80 to 63.50, incl	0.89
Over 63.50 to 76.20, incl	1.02
Over 76.20 to 101.60, incl	1.14

3.4.2.4 Decarburization and denitridation shall be measured by one of the following methods:

3.4.2.4.1 Metallographic (Microscopic) Method

A cross section taken perpendicular to the surface shall be etched and examined metallographically at a magnification not to exceed 200X in accordance with ASTM E1077. The sample shall not show decarburization and/or denitridation exceeding the limits of Table 4.

3.4.2.4.2 Hardness Traverse (Microindentation) Methods

The total depth of decarburization and denitridation shall be determined by a traverse method using microhardness testing in accordance with ASTM E1077. Samples shall be hardened and protected during heat treatment to prevent changes in surface carbon and nitrogen content. Samples may be tempered at the option of the producer. Measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization/denitridation on the adjacent surface. Acceptance shall be as listed in Table 4.

3.4.2.4.3 When determining the depth of decarburization/denitridation it is permissible to disregard local areas provided the decarburization/denitridation of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4.2.4.4 In case of dispute, the total depth of decarburization/denitridation using the microindentation hardness traverse method shall govern.

3.4.3 Response to Heat Treatment

Specimens as in 4.3.3, protected by suitable means or treated in neutral atmosphere to minimize scaling and prevent either carburization or decarburization, shall have hardness not lower than 58 HRC, or equivalent (see 8.2), after being heated to 1920 °F ± 25 °F (1049 °C ± 14 °C), held at heat for 30 minutes ± 3 minutes, quenched in oil, sub-zero cooled to -80 °F (-62 °C) or below for 2 hours ± 0.25 hour, and warmed in air to room temperature and tempered at 350 °F ± 10 °F (177 °C ± 6 °C) for 60 minutes ± 5 minutes.

3.5 Quality

The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Steel shall be premium aircraft quality conforming to AMS2300 or to AMSSTD2154 class AA.

3.5.2 Bars shall be free from seams, laps, tears, and cracks, after removal of the standard machining allowance in accordance with AS1182.

3.5.3 Grain flow of die forgings, except in areas that contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances

Bars and wire shall conform to all applicable requirements of AMS2241.

3.7 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.4.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (see 3.1), condition (see 3.3), macrostructure (see 3.4.1.1), microinclusion rating (see 3.4.1.2), microstructure (see 3.4.1.3), average grain size (see 3.4.1.4), decarburization and denitridation (see 3.4.2), response to heat treatment (see 3.4.3), frequency-severity cleanliness rating (see 3.5.1 and 8.3), UT (only when performed as an alternative to AMS2300 frequency-severity rating) (see 3.5.1), and tolerances (see 3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Grain flow of die forgings (see 3.5.3) is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Wire and Forging Stock

In accordance with AMS2371.

4.3.2 Forgings

In accordance with AMS2374.

4.3.3 Specimens for response to heat treatment (see 3.4.3) from bars, wire, and billets shall be not less than 0.375 inch (9.52 mm) in thickness. Minimum dimensions in other directions shall be either those of the product cross section or 1.125 x 1.125 inches (28.58 x 28.58 mm).

4.4 Reports

The producer of the product shall furnish with each shipment a report showing the producer's name and the country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations), and the results of tests for composition, macrostructure, micro-inclusion rating, and frequency-severity cleanliness rating of each heat (see 8.3) and for microstructure, decarburization denitridation, and response to heat treatment of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5925C, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.4.1 Report the nominal metallurgically worked cross-sectional size and the cut size, if different (see 3.3.1.3).

4.4.2 The producer of stock for forging shall furnish with each shipment a report showing the producer's name and the country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations), the results of tests for composition and macrostructure of each heat, and the results of any additional property requirements imposed by 8.8. This report shall include the purchase order number, heat number, AMS5925C, size, and quantity.

4.4.3 When material produced to this specification has exceptions are taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS5925C(EXC) because of the following exceptions:" and the specific exceptions shall be listed (see 5.2.1.1).

4.5 Resampling and Retesting

Shall be as follows:

4.5.1 Bars, Wire, and Forging Stock

In accordance with AMS2371.

4.5.2 Forgings

In accordance with AMS2374.

5. PREPARATION FOR DELIVERY

5.1 Sizes

Except when exact lengths or multiples of exact lengths are ordered, straight bars and wire will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).