

AEROSPACE MATERIAL SPECIFICATION



AMS 6331B

Issued JUL 1991
Noncurrent APR 1996
Cancelled MAY 2003

Superseding AMS 6331A

Steel, Welding Wire
0.50Cr - 0.55Ni - 0.20Mo - (0.33 - 0.38C) (SAE 8735)
Vacuum Melted, Environment Controlled Packaging
(Composition similar to UNS G87350)

CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of May, 2003. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications noting that it has been cancelled.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 6331B

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

1. SCOPE:

1.1 Form:

This specification covers a low-alloy steel in the form of welding wire.

1.2 Application:

Primarily for use as filler metal for gas-metal-arc or gas-tungsten-arc welding of steels of similar composition where the weld area is required to have strength and toughness comparable to those of the parent metal.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2370	Quality Assurance Sampling of Carbon and Low-Alloy Steel, Wrought Products Except Forgings and Forging Stock
AMS 2635	Radiographic Inspection
AMS 2813	Packaging of Welding Wire, Standard Method
AMS 2814	Packaging of Welding Wire, Premium Quality
AMS 2815	Identification, Welding Wire, Line Code System
AMS 2816	Identification, Welding Wire, Color Code System
AMS 6357	Steel Sheet, Strip, and Plate - 0.50Cr - 0.55Ni - 0.25Mo - (0.33 - 0.38C) (SAE 8735)
AMS 6358	Steel Sheet, Strip, and Plate - 0.50Cr - 0.55Ni - 0.25Mo - (0.38 - 0.43C) (SAE 8740)

2.1.2 Aerospace Recommended Practices:

ARP1876 Weldability Test for Weld Filler Metal Wire

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.33	0.38
Manganese	0.75	1.00
Silicon	0.20	0.35
Phosphorus	--	0.008
Sulfur	--	0.008
Phosphorus + Sulfur	--	0.012
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.15	0.25
Copper	--	0.35
Oxygen (3.1.2)	--	0.0025 (25 ppm)
Nitrogen (3.1.2)	--	0.0050 (50 ppm)
Hydrogen (3.1.2)	--	0.0010 (10 ppm)

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.1.2 Determination of oxygen, nitrogen, and hydrogen content not required for cut lengths.

3.2 Condition:

Cold finished, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.2.1 Wire shall be furnished on disposable spools for machine welding and in cut lengths for manual welding, as ordered.

3.2.2 Drawing compounds, oxides, dirt, and other foreign materials shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.2.3 Residual elements and dissolved gases deposited on, or absorbed by, the welding wire as a result of cleaning or cold working operations shall be removed by vacuum degassing.

3.2.4 Annealing, if required, shall be performed under vacuum or in an inert gas atmosphere.

3.3 Properties:

Wire shall conform to the following requirements:

- 3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.
- 3.3.2 Spooled Wire: Shall conform to 3.3.2.1 and 3.3.2.2.
- 3.3.2.1 Cast: Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length, 4 - 14 feet (1.2 - 4.3 m), to form one loop, when cut from the spool and laid on a flat surface, shall form a circle 15 - 50 inches (381 - 1270 mm) in diameter.
- 3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).
- 3.3.3 Tensile Properties: Specimens, prepared in accordance with 4.3.1 and tested in accordance with ASTM E 8 or ASTM E 8M, shall have average tensile strength not lower than 90% of the average of the control specimens of 4.3.1; elongation of the welded specimens shall be not less than 6% in 2 inches (50.8 mm).

3.4 Quality:

- 3.4.1 Steel shall be vacuum induction melted.
- 3.4.2 Wire, as received by purchaser, shall be uniform in quality and condition, sound, free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2.

3.5.1 Diameter:

TABLE I

Form	Nominal Diameter Inch	Tolerance	Tolerance
		Inch plus	Inch minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter Millimeters	Tolerance Millimeter plus	Tolerance Millimeter minus
Cut Lengths	0.76, 1.14, 1.57, 1.98	0.05	0.05
Cut Lengths	2.39, 3.18, 3.96, 4.78	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.013	0.013
Spools	0.76, 0.89, 1.14	0.025	0.05
Spools	1.57, 1.98, 2.39	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), tensile properties (3.3.3), sizes and tolerances (3.5), and alloy verification (5.2.1) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2370 and the following: