

AEROSPACE MATERIAL SPECIFICATION

SAE AMS 6381G

Issued	1942-12
Revised	2003-10
Reaffirmed	2008-04

Superseding AMS 6381F

Steel, Mechanical Tubing
0.95Cr - 0.20Mo (0.38 - 0.43C) (SAE 4140)
(Composition similar to UNS G41400)

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of mechanical tubing.

1.2 Application:

This tubing has been used typically for parts, 0.500 inch (12.70 mm) and under in section thickness at time of heat treatment, requiring a through-hardening steel capable of developing hardness as high as 50 HRC when properly hardened and tempered and also for parts of greater thickness but requiring proportionately lower hardness, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2253	Tolerances, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301	Steel Cleanliness, Aircraft Quality, Magnetic Particle Inspection Procedure
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.1 (Continued):

AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys

AS1182 Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM A 255 Determining Hardenability of Steel

ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E 112 Determining the Average Grain Size

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E 381 Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

ASTM E 384 Microindentation Hardness of Materials

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.38	0.43
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

Cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.2). Tubing ordered hot finished and annealed or tempered shall have hardness not higher than 99 HRB, or equivalent. Hardness shall be determined in accordance with ASTM E 18.

3.3 Properties:

Tubing shall conform to the following requirements.

- 3.3.1 Macrostructure: Visual examination of transverse full cross-sections from blooms or tube rounds, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure Limits

Section Size Square Inches	Section Size Square Centimeters	Macrographs
Up to 36, incl	Up to 232, incl	S2 - R1 - C2
Over 36 to 100, incl	Over 232 to 645, incl	S2 - R2 - C3

- 3.3.2 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112.

- 3.3.3 Hardenability: Shall be J 6/16 inch (9.5 mm) = 50 HRC minimum, determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalized at $1700^{\circ}\text{F} \pm 10$ ($927^{\circ}\text{C} \pm 6$) and the test specimen austenitized at $1550^{\circ}\text{F} \pm 10$ ($843^{\circ}\text{C} \pm 6$).

3.3.4 Decarburization:

- 3.3.4.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

- 3.3.4.2 Allowable decarburization of pierced billets, of tube rounds, and tubing for redrawing or forging, or of tubing ordered to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

- 3.3.4.3 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 3.

TABLE 3A - Maximum Depth of Decarburization, Inch/Pound Units

Nominal Wall Thickness Inches	Total Depth ID Inch	Total Depth OD Inch
Up to 0.109, incl	0.008	0.015
Over 0.109 to 0.203, incl	0.010	0.020
Over 0.203 to 0.400, incl	0.012	0.025
Over 0.400 to 0.600, incl	0.015	0.030
Over 0.600 to 1.000, incl	0.017	0.035
Over 1.000	0.020	0.040

TABLE 3B - Maximum Depth of Decarburization, SI Units

Nominal Wall Thickness Millimeters	Total Depth ID Millimeter	Total Depth OD Millimeter
Up to 2.77, incl	0.20	0.38
Over 2.77 to 5.16, incl	0.25	0.51
Over 5.16 to 10.16, incl	0.30	0.64
Over 10.16 to 15.24, incl	0.38	0.76
Over 15.24 to 25.40, incl	0.43	0.89
Over 25.40	0.51	1.02

- 3.3.4.4 Decarburization shall be measured by the metallographic method, by the HR30N scale hardness testing method, or by a traverse method using microhardness testing in accordance with ASTM E 384. The hardness method(s) shall be conducted on a hardened but untempered specimen protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization on the adjacent surface. In case of dispute, the depth of decarburization determined using the microhardness traverse method shall govern.

- 3.3.4.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

3.4.2 Mechanical tubing ordered hot rolled or cold drawn, or ground, turned, or polished, shall after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2370.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition, macrostructure, hardenability, and frequency-severity cleanliness rating of each heat and for hardness and average grain size for each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 6381G, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2370.