

SAE-AMS-QQ-A-250/8

ADOPTION NOTICE

SAE-AMS-QQ-A-250/8, "Aluminum Alloy 5052, Plate and Sheet", was adopted on 30-JUN-98 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, 700 Robbins Avenue, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

Custodians:

Army - MR
Navy - AS
Air Force - 11
DLA - IS

Adopting Activities:

DLA - IS
(Project 9535-0628-007)

SAENORM.COM : Click to view the full PDF of amsqqa250/8

FSC 9535

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited..



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS-QQ-A-250/8

Issued

AUG 1997

Submitted for recognition as an American National Standard

ALUMINUM ALLOY 5052, PLATE AND SHEET

UNS A95052

NOTICE

This document has been taken directly from Federal Specification QQ-A-250/8F and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards.

The original Federal Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, (b) the use of the existing government specification or standard format, and (c) the exclusion of any qualified product list (QPL) sections.

The complete requirements for procuring 5052 aluminum alloy plate and sheet described herein shall consist of this document and the latest issue of AMS-QQ-A-250.

1. SCOPE AND CLASSIFICATION:

1.1 Scope:

This specification covers the specific requirements for 5052 aluminum alloy plate and sheet; the general requirements are covered in AMS-QQ-A-250.

1.2 Classification:

1.2.1 Tempers: The plate and sheet are classified in one of the following tempers as specified (See 6.2): O, H22, H24, H26, H28, H32, H34, H36, H38, H112, or F temper. Definitions of these tempers are specified in AMS-QQ-A-250.

1.2.1.1 Material in either of a pair of tempers (H32 and H22, H34 and H24, H36 and H26, or H38 and H28) may be supplied at the option of the supplier, unless one is specifically excluded in the contract or purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1997 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:

(412) 772-7154
(412) 776-4970

FAX: (412) 776-0243
FAX: (412) 776-0790

AMS-QQ-A-250/8

SAE

AMS-QQ-A-250/8

2. APPLICABLE DOCUMENTS:

See AMS-QQ-A-250.

3. REQUIREMENTS:

3.1 Chemical Composition:

3.1.1 The chemical composition shall conform to the requirements specified in Table I.

TABLE I. Chemical Composition 1/

Element	Percent	
	Minimum	Maximum
Magnesium	2.12	2.8
Chromium	0.15	0.35
Iron	-	0.40
Silicon	-	0.25
Copper	-	0.10
Manganese	-	0.10
Zinc	-	0.10
Other Elements, each	-	0.05
Other Elements, total	-	0.15
Aluminum	Remainder	

1/ Analysis shall routinely be made only for the elements specifically mentioned in Table I. If, however, the presence of other elements is indicated or suspected in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits.

3.2 Mechanical Properties:

3.2.1 Mechanical Properties of Material as Supplied: The mechanical properties parallel to the direction of the final rolling shall conform to the requirements of Table II for the temper specified.

AMS-QQ-A-250/8

SAE

AMS-QQ-A-250/8

TABLE II. Mechanical Properties (See 6.4)

Temper	Thickness Inches	Tensile Strength			Elongation in 2 in. or 4 times D 1/ 3, minimum Percent
		Min	Max		
		ksi	ksi		
O	0.006 thru 0.007	25.0	31.0		
	0.008 thru 0.012	25.0	31.0		14
	0.013 thru 0.019	25.0	31.0		15
	0.020 thru 0.031	25.0	31.0		16
	0.032 thru 0.050	25.0	31.0		18
	0.051 thru 0.113	25.0	31.0		19
	0.114 thru 0.249	25.0	31.0		20
	0.250 thru 3.000	25.0	31.0		18
H22 or H32 2/	0.017 thru 0.019	31.0	38.0		4
	0.020 thru 0.050	31.0	38.0		5
	0.051 thru 0.113	31.0	38.0		7
	0.114 thru 0.249	31.0	38.0		9
	0.250 thru 0.499	31.0	38.0		11
	0.500 thru 2.000	31.0	38.0		12
H24 or H34 2/	0.009 thru 0.019	34.0	41.0		3
	0.020 thru 0.050	34.0	41.0		4
	0.051 thru 0.113	34.0	41.0		6
	0.114 thru 0.249	34.0	41.0		7
	0.250 thru 1.000	34.0	41.0		10
H26 or H36 2/	0.006 thru 0.007	37.0	44.0		2
	0.008 thru 0.031	37.0	44.0		3
	0.032 thru 0.162	37.0	44.0		4
H28 or H38	0.006 thru 0.007	39.0	-		2
	0.008 thru 0.031	39.0	-		3
	0.032 thru 0.128	39.0	-		4
H112	0.250 thru 0.499	28.0	-		7
	0.500 thru 2.000	25.0	-		12
	2.001 thru 3.000	25.0	-		16
F	All	4/	4/	4/	

1/ Not required for material 1/2 inch or less in width.

2/ For the H2 temper series, the maximum tensile values do not apply.

3/ D represents specimen diameter.

4/ No requirement.