

HOSE ASSEMBLY,  
TETRAFLUOROETHYLENE, LIGHTWEIGHT HIGH TEMPERATURE, HIGH PRESSURE,  
3,000 PSI (20 684 kPa), HYDRAULIC AND PNEUMATIC

1. SCOPE

φ

This specification defines the requirements for lightweight hose assemblies suitable for use in high temperature, 400° F (204° C), high-pressure, 3000 psi (20 684 kPa), aircraft and missile hydraulic and pneumatic systems.

2. APPLICABLE DOCUMENTS

The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein.

2.1 SPECIFICATIONS

2.1.1 FEDERAL

PPP-T-60	Tape, Packaging, Waterproof
QQ-W-423	Wire, Steel, Corrosion-Resisting
PPP-B-566	Boxes, Folding, Paperboard
PPP-B-576	Box, Wood, Cleated, Veneer, Paper Overlaid
PPP-B-585	Boxes, Wood, Wirebound
PPP-B-591	Boxes, Shipping Fiberboard, Wood-Cleated
PPP-B-601	Boxes, Wood, Cleated-Plywood
PPP-B-636	Boxes, Shipping, Fiberboard
PPP-B-665	Boxes, Paperboard, Metal-Edged and Components
PPP-B-676	Boxes, Set-Up
P-D-680	Dry Cleaning Solvent
QQ-S-763	Steel Bars, Wire Shapes, and Forgings, Corrosion-Resisting
TT-I-735	Isopropyl Alcohol

2.1.2 MILITARY

MIL-P-116	Preservation - Packaging, Methods of
MIL-C-5501	Caps and Plugs, Protective, Dust and Moisture Seal, General Specification for
MIL-H-5606	Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance
MIL-L-7808	Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
MIL-H-8446	Hydraulic Fluid, Nonpetroleum Base, Aircraft
MIL-T-8504	Tubing, Steel Corrosion-Resisting (304) Aerospace Vehicle Hydraulic Systems, Annealed, Seamless and Welded
φ MIL-T-8606	Tubing, Steel, Corrosion-Resistant (18-8 Stabilized and Extra Low Carbon)
MIL-T-8808	Tubing, Steel, Corrosion-Resistant (18-8 Stabilized), Aircraft Hydraulic Quality
MIL-F-8815	Filter and Filter Elements, Fluid Pressure, Hydraulic Line, 15 Micron Absolute and 5 Micron Absolute, Type II Systems
MIL-S-8879	Screw Threads, Controlled Radius Root with Increased Minor Diameter; General Specification of
MIL-L-10547	Liner, Case and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible
MIL-T-27602	Trichloroethylene, Oxygen Propellant Compatibility
MIL-H-83282	Hydraulic Fluid, Fire-Resistant, Synthetic, Hydrocarbon Base, Aircraft

2.2 STANDARDS

2.2.1 MILITARY

D00-STD-100	Engineering Drawing Practices
MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage
MIL-STD-130	Identification Marking of U.S. Military Property
MIL-STD-831	Test Reports, Preparation of

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

## 2.2.1 (Cont'd)

MS21900	Adapter, Flareless Tube to AN Flared Tube
MS33514	Fitting End, Standard Dimensions for Flareless Tube Connection and Gasket Seal
MS33656	Fitting End, Standard Dimensions for Flared Tube Connection and Gasket Seal

(Copies of documents required by suppliers in connection with specific procurement functions shall be obtained from the procuring activity or as directed by the Contracting Officer)

## 2.3

OTHER PUBLICATIONS

The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply:

Uniform Classification Committee

Uniform Freight Classification Rules

(Application for copies of the above publication should be addressed to the Uniform Classification committee, 202 Chicago Union Station, Chicago, IL 60606)

American Society for Testing and Materials

D412	Standard Test Methods for Rubber Properties in Tension
D571	Standard Methods of Testing Rubber Hose for Automotive Hydraulic Brake Systems
D792	Standard Test Methods for Specific Gravity and Density of Plastics by Displacement
D1457	Standard Specification For TFE - Fluorocarbon Resin Molding and Extrusion Materials

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103)

Society of Automotive Engineers

AMS 3380	Hose, Polytetrafluoroethylene, TFE Fluorocarbon-Resin, Wire Braid Reinforced
AMS 5556	Steel Tubing, Seamless or Welded, Corrosion and Heat-Resistant 18 Cr - 11 Ni - (Cb + Ta) (SAE 30347) Hydraulic
AMS 5557	Steel Tubing, Seamless and Welded, Corrosion and Heat-Resistant 18 Cr - 11 Ni-Ti (SAE 30321) Hydraulic
AMS 5567	Steel Tubing, Seamless and Welded, Corrosion Resistant 19 Cr - 10 Ni (SAE 30304) Hydraulic, Solution Treated
AMS 5570	Steel Tubing, Seamless, Corrosion and Heat-Resistant 18.5 Cr - 11 Ni - 0.40 Ti (SAE 30321)
AMS 5571	Steel Tubing, Seamless, Corrosion and Heat-Resistant 18 Cr - 11 Ni - 0.70 (Cb + Ta) (SAE 30347)
AMS 5575	Steel Tubing, Welded, Corrosion and Heat-Resistant, 18 Cr-10.5 Ni-0.70 (Cb+Ta) (SAE 30347)
AMS 5576	Tubing, Welded 18 Cr - 11 Ni - 0.40 Ti
AMS 5636	Steel Bars, Corrosion-Resistant 18 Cr - 8.5 Ni (SAE 30302) Cold Drawn, 100,000 psi (690 MN/m <sup>2</sup> )
AMS 5637	Steel Bars, Corrosion-Resistant 18 Cr - 8.5 Ni (SAE 30302), Cold Drawn, 125,000 psi (862 MPa)
AMS 5639	Steel Bars, Forgings, Tubing, and Rings, Corrosion-Resistant 19 Cr - 10 Ni (SAE 30304)
AMS 5643	Steel Bars, Forgings, Tubing and Rings, Corrosion Resistant 16.5 Cr - 4.0 Ni - 4.0 Cu
AMS 5644	Steel, Bars and Forgings, Corrosion and Heat Resistant 17 Cr - 7 Ni - 1Al
AMS 5645	Steel Bars, Forgings, Tubing and Rings, Corrosion and Heat Resistant 18 Cr - 10 Ni - 0.40 Ti (SAE 30321)
AMS 5646	Steel Bars, Forgings, Tubing and Rings, Corrosion and Heat Resistant 18 Cr - 11 Ni - 0.60 (Cb + Ta) (SAE 30347)
AMS 5647	Steel Bars, Forgings, Tubing and Rings, 18 Cr - 8 Ni
AMS 5659	Steel Bars, Forgings, and Rings, Corrosion Resistant 15Cr - 4.5Ni - 0.30(Cb + Ta) - 3.5Cu, Consumable Electrode Melted
AMS 5685	Wire, Safety 18 Cr - 11.5 Ni - 0.40 Ti, Solution Heat Treated
AMS 5688	Steel Wire, Corrosion-Resistant 18 Cr - 9.0 Ni (SAE 30302) Spring Temper
AMS 5689	Steel Wire, Corrosion and Heat Resistant 18 Cr - 9.5 Ni - Ti (SAE Solution Heat-Treated
AMS 5690	Steel Wire, Corrosion and Heat-Resistant 18.5 Cr - 13 Ni - 2.5 No (SAE 30316)
AMS 5697	Steel Wire, Corrosion-Resistant 19 Cr - 9.5 Ni (SAE 30304)

## 2.3 (Cont'd)

AMS 5743	Steel Bars and Forgings, Corrosion and Moderate Heat-Resistant 15.5 Cr - 4.5 Ni - 2.9 No - 0.10 N, Solution Heat-Treated, Sub-Zero Cooled, Equalized, and Over-Tempered
ARP 603	Impulse Testing of Hydraulic Hose Assemblies, Tubing and Fittings
ARP 611	Tetrafluoroethylene Hose Assembly Cleaning Methods
ARP 908	Hose Fitting - Installation and Qualification Test Torque Requirements
ARP 1153	Method for Determining Relative Specific Gravity, Polytetrafluoroethylene Tubing
AIR 1228	Standard Impulse Machine Equipment and Operation
AS115	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flareless, Straight to Straight, Lightweight
AS116	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flareless, Straight to 45°, Lightweight
AS117	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flareless, Straight to 90°, Lightweight
AS118	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flareless, 45° to 45°, Lightweight
AS119	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flareless, 45° to 90°, Lightweight
AS120	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flareless, 90° to 90°, Lightweight
AS153	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flared, Straight to Straight, Lightweight
AS154	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flared, Straight to 45°, Lightweight
AS155	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flared, Straight to 90°, Lightweight
AS156	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flared, 45° to 45°, Lightweight
AS157	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flared, 45° to 90°, Lightweight
AS158	Hose Assembly, Nonmetallic - 3,000 psi, TFE, Flared, 90° to 90°, Lightweight
AS1055	Fire Testing of Flexible Hose, Tube Assemblies, Coils, Fittings and Similar System Components
AS1624	Hose, Polytetrafluoroethylene (TFE), Lightweight 3,000 psi, High Temperature, Hydraulic and Pneumatic

(Application for copies should be addressed to the Society of  
Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096).

National Aerospace Standards

NAS1760 Fitting End, Flareless Acorn, Standard Dimensions for

(Application for copies should be addressed to National Standards Association, Inc.,  
5161 River Road, Washington, DC 20016)

3. REQUIREMENTS

3.1 QUALIFICATION

The hose assemblies furnished under this specification shall be products which are  
qualified by meeting all the requirements covered by this document.

3.2 MATERIALS

The hose assembly materials shall be uniform in quality, free from defects,  
consistent with good manufacturing practice and shall conform to applicable  
specifications and the requirements specified herein. All materials not  
specifically described herein shall be of the highest quality and suitable for the  
purpose intended.

3.2.1 METALS

Metals used in the hose and fittings shall be corrosion-resistant and shall conform  
to the following specification:

Bars and Forgings:

QQ-S-763	Class 302 - Cond. A and Cond. B (AMS 5636 and AMS 5637)
QQ-S-763	Class 304 - Cond. A and Cond. B (AMS 5639)
QQ-S-763	Class 304L - Cond. A (AMS 5647)

## 3.2.1 (Cont'd)

QQ-S-763	Class 321 - Cond. A (AMS 5645)
QQ-S-763	Class 347 - Cond. A (AMS 5646)
AMS 5643	17-4 PH
AMS 5644	17-7 PH
AMS 5659	15-5 PH
AMS 5743	AM-355

Tubing

MIL-T-8504	Comp. 304 (AMS 5567)
MIL-T-8606	Type I, Comp. 321 (AMS 5570)
MIL-T-8808	Type I or Type II, Comp. 321 (AMS 5557, AMS 5570 or AMS 5576)
MIL-T-8808	Type I or Type II, Comp. 347 (AMS 5571 or AMS 5575, AMS 5556)

Wire

QQ-W-423	Comp. 302 (AMS 5688)
QQ-W-423	Comp. 304 (AMS 5697)
QQ-W-423	Comp. 305 (AMS 5685)
QQ-W-423	Comp. 316 (AMS 5690)
AMS 5689	Comp. 321 (QQ-W-423, Form 1, Comp. 321)

## 3.3

CONSTRUCTION

The hose assembly shall consist of a seamless tetrafluoroethylene inner tube, corrosion-resistant steel-wire reinforcement, and corrosion-resistant steel end fittings as required for the intended installation.

## 3.3.1

INNER TUBE

The inner tube shall be of a seamless construction of virgin tetrafluoroethylene resin of uniform gauge. It shall have a smooth bore and shall be free from pitting or projections on the inner surface. Additives may be included in the compound from which the tube is extruded.

## 3.3.2

REINFORCEMENT

The reinforcement shall consist of corrosion-resistant steel wires conforming to the applicable specifications listed in 3.2.1. The wires shall be so arranged over the inner tube as to provide sufficient strength to ensure conformance with the requirements specified herein. Broken reinforcing wires shall be cause for rejection. Crossed-over reinforcing wires shall not be cause for rejection of the hose assembly.

## 3.3.3

INTERLAYERS

Interlayers, if used, shall be of a suitable material and shall be resistant to pressure pounding and to all fluids with which the hose may come in contact during normal service. They shall be capable of withstanding temperatures of -65 F (-54°C) to 400 F (204°C) and shall not extrude through the outer braid during testing or in service.

## 3.3.4

FITTINGS

All fittings shall be proven to meet the requirements herein. Standard hose assemblies shall have flared fittings to mate with MS33656 or flareless fittings according to NAS 1760 to mate with MS33514 in accordance with applicable SAE Standards (see 2.2). Fitting hex portions shall fit standard wrench openings.

## 3.3.4.1

Standard Fittings

Standard fittings shall be of one piece construction. Weld or braze joints must not be located in the fluid paths, except welded and redrawn tubing in accordance with MIL-T-8504 or MIL-T-8808 may be used.

## 3.3.4.2

Non-Standard Fittings

Non-standard elbow fittings shall be of one piece construction to the maximum extent possible. However, those made with other than one piece construction can use welded and redrawn tubing in accordance with MIL-T-8504 or MIL-T-8808 and shall employ a butt-weld joint method.

## 3.3.4.3

End Fitting Collars (Sockets)

All end fitting collars (sockets) crimped or swaged, fabricated from Type 304 stainless steel are required to be capable of passing an embrittlement test as specified in ASTM A 262 Practice E, prior to assembly to the nipple or swaging operation. Sockets fabricated from stabilized austenitic steel (304 L, 321, or 347) are acceptable without being subjected to the embrittlement test.

3.4 DIMENSIONS

The hose assembly dimensions, except for length, shall be as specified in Figure 6.

3.4.1 HOSE WEIGHT

Hose consisting of inner tube, reinforcement and interlayers as outlined in paragraphs 3.3.1 through 3.3.3 shall not exceed the maximum hose weights covered in Table I.

TABLE I  
PHYSICAL REQUIREMENTS OF HOSE ASSEMBLIES AND WEIGHT OF HOSE

HOSE SIZE	HOSE WEIGHT MAX. ①		OPERATING PRESSURE MAX.		PROOF PRESSURE MIN.		BURST PRESSURE				BEND RADIUS AT INSIDE OF BEND		VOLUMETRIC EXPANSION MAX.	
							ROOM TEMPERATURE MIN.		HIGH TEMPERATURE MIN.					
	LBS/IN	Kg/M	PSI	kPa	PSI	kPa	PSI	kPa	PSI	kPa	IN.	MM.	CC/IN	CC/CM
-4	.009	.18	3,000	20 684	6,000	41 369	16,000	110 316	12,000	82 737	1.50	38.1	.065	.026
-6	.015	.27	3,000	20 684	6,000	41 369	14,000	96 527	10,500	72 395	2.50	63.5	.085	.033
-8	.020	.38	3,000	20 684	6,000	41 369	14,000	96 527	10,500	72 395	2.88	73.2	.135	.053
-10	.027	.48	3,000	20 684	6,000	41 369	12,000	82 737	9,000	62 053	3.25	82.6	.220	.087
-12	.055	1.00	3,000	20 684	6,000	41 369	12,000	82 737	9,000	62 053	4.00	101.6	.300	.118
-16	.085	1.52	3,000	20 684	6,000	41 369	12,000	82 737	9,000	62 053	5.00	127.0	.750	.295

① Hose Weight shall be determined on a minimum length of 12 inches (305 mm)

3.5 PERFORMANCE

The hose assembly shall meet the following performance requirements:

3.5.1 TUBE3.5.1.1 Tube Roll

φ

The tube shall not leak, split, burst, or show any evidence of malfunction, when rolled to the Table IV flattening and rounding gaps. Test method is specified in 4.6.2.1.

3.5.1.2 Tube Proof Pressure

φ

The tube, without reinforcing wires, shall not leak, burst or show any evidence of malfunction when held at the Table IV proof pressure values for one (1) minute. Test method is specified in 4.6.2.1.

3.5.1.3 Tensile Strength

φ

The longitudinal tensile strength for all sizes of tubes shall be 2,200 psi (15 168 kPa) minimum at 77°F +2°F (25°C +1°C). The transverse tensile strength for sizes -10 and larger shall be 1,800 psi (12 411 kPa) minimum at the same temperature. For sizes -8 and smaller the transverse tensile strength need not be tested. Test method is specified in 4.6.2.2.

3.5.1.4 Elongation

φ

Elongation at 77°F +2°F (25°C +1°C) shall be a minimum of 200 percent. Test method is specified in 4.6.2.3.

- 3.5.1.5 Specific Gravity
- φ The specific gravity values of the hose inner tube shall not exceed 2.155 apparent and 2.210 specific. Test method is specified in 4.6.2.4.
- 3.5.2 HOSE ASSEMBLY
- φ The hose, complete with reinforcing wires and assembled with end fittings, shall meet the following performance requirements:
- 3.5.2.1 Proof Pressure
- φ The hose assembly shall withstand the proof pressure listed in Table I without malfunction or leakage. Test method is specified in 4.6.3.
- 3.5.2.2 Elongation and Contraction
- φ The hose assembly shall not change in length by more than +0.20 inch (+5.1 mm) in 10 inches (254 mm) of hose length, when subjected to the operating pressure in Table I for minimum of 5 minutes. Test method is specified in 4.6.4.
- 3.5.2.3 Volumetric Expansion
- φ The volumetric expansion of the hose assemblies, shall not exceed the limits specified in Table I. Test method is specified in 4.6.5.
- 3.5.2.4 Leakage
- φ The hose assembly shall not leak when subjected to two (2) pressure cycles of 70 percent of minimum room temperature burst pressure. Test method is specified in 4.6.6.
- 3.5.2.5 Room Temperature Burst Pressure
- φ The hose assembly shall not leak nor burst at any pressure below the burst value specified in Table I. Test method is specified in 4.6.7.
- 3.5.2.6 Thermal Shock
- φ The hose assemblies shall not leak nor show any evidence of malfunction when subjected to the Table I proof and high temperature burst pressures after being thermally shocked by rapidly increasing hose temperature from -65° F (-54° C) to 400° F (204° C). Test method is specified in 4.6.8.
- 3.5.2.7 Impulse
- φ The hose assemblies shall show no evidence of leakage from hose or fitting prior to completion of 250,000 pressure impulse cycles. Test method is specified in 4.6.9.
- 3.5.2.8 Assembly Flexibility
- φ The hose assembly shall not leak nor show any evidence of malfunction when subjected to the Table I proof pressure after 400,000 flexure cycles when tested from -67° F (-54° C) to 400° F (204° C). Test method is specified in 4.6.10.
- 3.5.2.9 Stress Degradation
- φ The air leakage rate from the hose and two end fittings (not including "B" nuts) when held at the Table I operating pressure after completion of the stress degradation test shall not exceed 2.0 cc/in./min. (0.78 cc/cm/min). Test method is as specified in 4.6.11.
- 3.5.2.10 Pneumatic Surge
- φ There shall be no evidence of inner tube collapse, sponging or shedding of Teflon particles from the inner tube after 16 cycles of rapid reduction of pneumatic pressure from the Table I operating pressure to zero (0) psi. Test method is as specified in 4.6.12.
- 3.5.2.11 Effusion
- φ The effusion rate for any hose size shall not exceed 8.0 cc/ft. (26 cc/m) of hose length. Test method is as specified in 4.6.13.
- 3.5.2.12 Overtightening Torque
- φ The fitting shall withstand the overtightening torque values specified in ARP 908. Test method is specified in 4.6.14.

## 3.5.2.13

Conductivity

φ

Hose assembly sizes -4 through -8 shall be capable of conducting a direct current equal to or greater than six (6) microamperes and sizes -10 through -16, a direct current equal to or greater than twelve (12) microamperes with a test potential of 1,000 volts dc. Test method is specified in 4.6.15.

## 3.6

SCREW THREADS

Coupling nut threads shall be in accordance with MIL-S-8879. Thread tolerance increase of 10% during assembly or testing shall not be cause for rejection of the hose assembly.

## 3.7

LENGTH

Hose assembly length shall be specified in the following increments only:

Under 18 inches (457 mm), not less than 1/8 inch (3.2 mm)  
18 to 36 inches (457 to 914 mm), not less than 1/4 inch (6.4 mm)  
36 to 50 inches (914 to 1 270 mm), not less than 1/2 inch (12.7 mm)  
Over 50 inches (1 270 mm), not less than 1 inch (25.4 mm)

NOTE: Flareless hose assembly lengths shall be made from "gage point" to "gage point."

Tolerances on hose assembly lengths shall be as follows:

+1/8 inch (3.2 mm) for lengths under 18 inches (457 mm)  
+1/4 inch (6.4 mm) for lengths from 18 to 36 inches (457 to 914 mm)  
+1/2 inch (12.7 mm) for lengths from 36 to 50 inches (914 to 1 270 mm)  
+1% for lengths over 50 inches (1 270 mm)

## 3.8

PART NUMBERING OF INTERCHANGEABLE PARTS

All parts having the same manufacturer's part number shall be functionally and dimensionally interchangeable. The item identification and part number requirement of DOD-STD-100 shall govern the manufacturer's part numbers and changes thereto.

## 3.9

IDENTIFICATION OF PRODUCT

Equipment, assemblies and parts shall be marked for identification in accordance with MIL-STD-130. The following special marking shall be added:

## 3.9.1

FITTINGS

The manufacturer's name or trademark shall be permanently marked on all end fittings.

## 3.9.2

ASSEMBLY

A permanent marking on the fitting or a permanent band on the hose shall be used. The band shall be no wider than one inch (25 mm) and shall not impair the flexibility or the performance of the hose. The marking on the fitting or band shall include the following information:

- a. Assembly manufacturer's name or trademark, and assembly specification "AS 1339"
- b. Complete hose assembly part number.
- c. Operating pressure "3000 psi" or "20 684 kPa," as applicable.
- d. Operating temperature "400° F" or "204° C" as applicable.
- e. Pressure test symbol "PT."
- f. Date of hose assembly manufacture expressed in terms of month and year.
- g. Hose manufacturer's federal code number (Handbook H4-1)

## 3.10

WORKMANSHIP

The hose assembly, including all parts, shall be constructed and finished in a thoroughly workmanlike manner. All surfaces shall be free from burrs. All sealing surfaces shall be smooth, except that annular tool marks up to 100 microinches (2.5 micrometers) rms maximum will be acceptable.

## 3.10.1

DIMENSIONS AND TOLERANCES

All pertinent dimensions and tolerances, where interchangeability, operation or performance of the hose assembly may be affected, shall be specified on all drawings.

3.10.2 CLEANING

All hose assemblies shall be free from oil, grease, dirt or other foreign materials both, internally and externally. Unless otherwise specified, hose assemblies shall be cleaned to Class 0 of ARP 611.

4. QUALITY ASSURANCE PROVISIONS

4.1 RESPONSIBILITY FOR INSPECTION

Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the procuring activity. The procuring activity reserves the right to perform any of the inspections set forth in the specification, where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 CLASSIFICATION OF INSPECTIONS

The examining and testing of hose assemblies shall be classified as:

- a. Qualification inspections (see 4.3).
- b. Quality conformance inspections (see 4.4).

4.3 QUALIFICATION INSPECTIONS

4.3.1 QUALIFICATION TEST SAMPLES

The number and length of test samples required to qualify each hose size are specified in Table II. All specimens for each hose size are required for qualifying each of the methods of end fitting attachment, permanent or field attachable, and for each method of end fitting construction, bent tube or forged. Simultaneous qualification of flared and flareless end fittings may be accomplished by having fittings on one hose end flared and flareless fittings on the other end. If a supplier qualifies one end fitting outlet design and at a later date desires to qualify the other, two hose assemblies of each size to be qualified shall be subjected to the tests specified in paragraph 4.5.2.2.

TABLE II

LENGTH OF HOSE ASSEMBLIES FOR TEST (IN INCHES) ① ② φ

HOSE ASSEMBLY SIZE	SIX ASSEMBLIES FOR IMPULSE TEST (4.6.9)	TWO ASSEMBLIES FOR FLEX TEST (4.6.10)	SIX ASSEMBLIES FOR OTHER TESTS ③ ④
-4	12	16	18
-6	15	19	18
-8	18	21	18
-10	21	23	18
-12	25	27	18
-16	31	32	18

- ① End fitting outlet design shall have flared fittings to mate with MS33656 or flareless fittings according to NAS 1760 to mate with MS33514.
- ② The six test specimens required for the impulse test (4.6.9) shall have straight end fittings on one end and 90° elbow end fittings on the other end. All remaining test samples shall have straight-to-straight end fittings.
- ③ One additional sample of each size in lengths as shown in Figure 5 shall be used for examination and conductivity tests (sample No. 16 Table III).
- ④ Two additional samples of each size are required if tests in accordance with paragraph 4.5.2.2 are conducted.

4.3.2 QUALIFICATION TEST SEQUENCE

Test sequence and procedure shall be as specified in Table III and if applicable paragraph 4.5.2.2.

TABLE III  
QUALIFICATION TEST SCHEDULE

SAMPLE NO.	TUBE	ASSEMBLIES ①										
	1	2	3	4	5	6	7	8	9	10 THRU 15	16	
PARA.	4.6.1.1	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2	4.6.1.2
	4.6.2	4.6.3	4.6.3	4.6.3	4.6.3	4.6.3	4.6.3	4.6.3	4.6.3	4.6.3	4.6.3	4.6.15
		4.6.4	4.6.4	4.6.5	4.6.5	4.6.6	4.6.6	4.6.6	4.6.11	4.6.11	4.6.9	
		4.6.10	4.6.10	4.6.13	4.6.13	4.6.8	4.6.8	4.6.8	4.6.12	4.6.12		
		4.6.14	4.6.14	4.6.7	4.6.7							

① Production inspection records shall be used to verify tube conformance to 4.6.2 for all assemblies.

4.3.3 TEST REPORT, TEST SAMPLES AND DATA FOR THE PROCURING ACTIVITY

When the tests are conducted at a location other than the laboratory of the procuring activity, the following shall be furnished to that activity:

a. Test Report

Three (3) copies of a test report in accordance with MIL-STD-831, which shall include a report of all tests and outline description of the tests and conditions. (See note below)

b. Test Samples

Test samples when requested by the procuring activity.

c. Drawings

Three (3) sets of assembly and subassembly drawings. The assembly drawings shall have a cut-away section showing all details in their normal assembly position and shall carry part numbers of all details and subassemblies.

d. Sources

List of sources of hose or hose components, including sources' name and product identification for inner tube, hose and assembly.

Note: Log sheets and recorded test data shall remain on file at the source test facility and are not to be sent to the qualifying activity unless specifically requested.

4.3.4 QUALIFICATION INSPECTION METHODS

Qualification inspection methods shall consist of all the examinations and tests specified under 4.6.

4.4 QUALITY CONFORMANCE INSPECTIONS

Quality conformance inspections shall be sampled in accordance with the procedure in MIL-STD-105 and shall consist of the following tests:

a. Individual tests (see 4.4.1) (100 percent inspection)

b. Sampling tests (see 4.4.2)

c. Periodic control tests (see 4.4.3)

4.4.1 INDIVIDUAL TESTS

Each hose assembly shall be subjected to the following tests as noted:

- φ a. Examination of product (See 4.6.1)
- b. Proof pressure test (See 4.6.3)

Note: Production hose assemblies that are proof pressure tested with water shall be air dried prior to capping (see cleaning requirements, paragraph 3.10.2).

4.4.2 SAMPLING TESTS

The following inspections and tests shall be performed in the order as indicated on eight (8) hose assemblies, selected at random from each inspection lot. The inspection lot shall consist of no more than 3,000 hose assemblies, all of one dash number size, manufactured under essentially the same conditions. One (1) hose assembly tested from each lot of 375 hose assemblies is also permitted.

- φ a. Internal cleanliness (ARP 611, Class 0)
- b. Leakage tests (see 4.6.6)
- c. Room-temperature burst pressure test (see 4.6.7)
- d. Specific gravity tests (Apparent and Relative) (see 4.6.2.4)

4.4.3 PERIODIC CONTROL TESTS

The following inspections and tests shall be performed as indicated on eight (8) hose assemblies manufactured from bulk hose lengths selected at random from each inspection lot. The inspection lot shall consist of not more than 20,000 feet of hose, all of one dash number size, manufactured under essentially the same conditions. Two (2) hose assemblies manufactured and tested from each lot of 5,000 feet of hose is also permitted.

4.4.3.1 Four (4) hose assemblies (or one (1) hose assembly from a lot of 5,000 feet) in accordance with Table II shall be subjected to the following tests in the order indicated:

- φ a. Elongation and contraction test (see 4.6.4)
- b. Impulse test (see 4.6.9) (unaged samples only)

4.4.3.2 Four (4) hose assemblies (or one (1) hose assembly from a lot of 5,000 feet) in accordance with Table II shall be subjected to the following tests in the order indicated:

- a. Stress degradation test (see 4.6.11)
- b. Conductivity test (see 4.6.15)

4.4.4 REJECTION AND RETEST

Where one or more items selected from a lot fails to meet the specification, all items in the lot shall be rejected.

4.4.4.1 Resubmitted Lots

Once a lot (or part of a lot) has been rejected by a procuring activity (Government or industrial), before it can be resubmitted for tests, full particulars concerning the cause of previous rejection and the action taken to correct the defects in the lot shall be furnished, in writing, by the contractor.

4.4.5 SWITCHING PROCEDURES

Switching inspection severity levels (for example, from normal to tightened inspection) shall be in accordance with MIL-STD-105. All inspection plans shall be single sample plans with an AQL of 1.5 percent at special inspection level S-2.

4.4.6 DESTRUCTIVE TEST SAMPLE

Prior to testing, a letter "D" shall be impression-stamped on each end fitting of those assemblies used for destructive tests (see 4.4.2 and 4.4.3).

#### 4.5 TEST CONDITIONS

##### 4.5.1 FITTING ENDS

- ϕ Qualification tests shall be conducted in accordance with test sequence specified in Table III on test sample configurations as specified in Table II. Satisfactory completion of qualification tests shall also constitute qualification approval for hose assemblies having nonstandard fittings that have an identical attachment method and design and meet the requirements of this specification.

##### 4.5.2 PREPARATION OF SAMPLE

4.5.2.1 Unless otherwise specified, length of sample assemblies shall be in accordance with Table II.

4.5.2.2 ϕ If test samples have all one type end fitting (flared or flareless) and qualification approval is desired for the other type end fitting, two (2) additional hose assemblies with the other type fitting end and of the size to be qualified shall be subjected to the following tests in the sequence indicated.

- a. Examination of product - (See 4.6.1)
- b. Proof pressure test - (See 4.6.3)
- c. Leakage test - (See 4.6.6)
- d. Overtightening torque test - (See 4.6.14)
- e. Room temperature burst pressure test - (See 4.6.7)

##### 4.5.2.3 Oil Aging

In all the tests using oil aged samples, the hose assemblies shall be filled with a high temperature test fluid and soaked in an air oven at a temperature of 400°F (204°C) for seven (7) days. All air shall be excluded from the bore of the assembly during the test. No pressure shall be applied to the assembly during the aging period.

##### 4.5.2.4 Air Aging

Air aged samples shall be kept in air at a temperature of 400°F (204°C) for seven days.

##### 4.5.2.5 Unaged Samples

Unaged assemblies shall be as shipped from the hose assembly manufacturer.

#### 4.5.3 ϕ TEST FLUIDS AND PRESSURE MEASUREMENTS

Unless otherwise specified, the pressure test fluid shall be hydraulic oil conforming to MIL-H-5606, or water. Where a high temperature test fluid is specified, the test fluid shall be MIL-H-8446 hydraulic fluid, MIL-L-7808 lubricating oil, or one of the following:

- a. Dow Chemical F-60 or equal
- b. Oronite Chemical 8200 or equal
- c. MIL-H-83282 or equal

Unless otherwise specified, all pressures shall have a tolerance of ±100 psi (±689 kPa).

#### 4.5.4 TEMPERATURE MEASUREMENTS

Unless otherwise specified, temperature measurements shall be taken within six inches (152 mm) of the hose assemblies under test. Unless otherwise specified, all temperatures shall have a tolerance of +15°F (+8°C), -5°F (-3°C).

#### 4.5.5 END CONNECTIONS

Except as otherwise noted, each hose end shall be connected to a steel male fitting end in accordance with MS33656 or MS33514, lubricated with either MIL-H-5606 fluid or the test fluid, with the installation torque range specified in ARP 908.

4.6 INSPECTION METHODS4.6.1 EXAMINATION OF PRODUCT4.6.1.1 Inner Tube (TFE)

Each length of tubing shall be examined to determine conformance to this specification with respect to material, size, workmanship and dimensions.

4.6.1.2 Hose Assembly

All hose assemblies shall be visually inspected to determine conformance to this specification and inspected for broken or missing reinforcing wires or any evidence of malfunction which shall be cause for rejection. Crossed over reinforcing wires shall not be cause for rejection.

4.6.2 TUBE TESTS4.6.2.1 Tube Roll and Proof Pressure Test

Each length of tubing shall be subjected to a tube roll and proof pressure test in accordance with AMS 3380, except that the flattening gap, rounding gap, and proof pressure shall be as specified in Table IV. The test fluid shall be air or water.

TABLE IV

TUBE ROLL GAP AND PROOF PRESSURE

SIZE	FLATTENING GAP-MAX		ROUNDING GAP-MIN		PROOF PRESSURE	
	INCHES	mm	INCHES	mm	PSI	kPa
φ -4	.281	7.14	.250	6.35	380	2 620
-6	.281	7.14	.328	8.33	280	1 931
-8	.328	8.33	.469	11.91	220	1 517
-10	.328	8.33	.578	14.68	170	1 172
-12	.328	8.33	.688	17.48	130	896
-16	.328	8.33	.828	21.03	95	655

4.6.2.2 Tensile Strength

Size -10 tube, and under, shall be subjected to tensile strength tests in accordance with ASTM D412, except that the separation speed shall be two inches (51 mm) per minute. Tubes larger than -10 shall be tested in accordance with ASTM D1457. The longitudinal tensile strength for all sizes shall be a minimum of 2,200 psi (15 168 kPa) at 77°F ±2°F (25°C ±1°C). The transverse tensile strength shall be 1,800 psi (12 411 kPa) at the same temperature. In sizes under -10, the transverse tensile strength need not be tested.

4.6.2.3 Elongation

The tube shall be subjected to the elongation in accordance with the ASTM methods specified in 4.6.2.2. Elongation at a temperature of 77°F ±2°F (25°C ±1°C) shall be a minimum of 200 percent.

4.6.2.4 Specific Gravity of the Tube4.6.2.4.1 Apparent specific gravity

Apparent specific gravity shall be determined in accordance with ASTM D792, method A, and shall not exceed 2.155 at 77°F ±2°F (25°C ±1°C). Two (2) drops of wetting agent shall be added to the water.

4.6.2.4.2 Relative specific gravity

Relative specific gravity shall be determined in accordance with the ARP 1153 method and shall not exceed a value of 2.210 for all sizes and types of tubes.

#### 4.6.3 PROOF PRESSURE TEST

All hose assemblies shall be pressure tested to the values specified in Table I for not less than 30 seconds and not more than five (5) minutes. The test fluid may be either water or hydraulic oil conforming to MIL-H-5606 for tests conducted at room temperature. All assemblies used for the tests described in this specification shall have this proof pressure test applied to them. Any evidence of leakage from hose or fittings, or any other evidence of malfunction shall constitute failure. Proof pressure test of hose assemblies having firesleeves shall use water as the test medium. Proof pressure shall be held for a minimum of two (2) minutes, during which time the firesleeves shall be pulled back from the end fittings.

#### 4.6.4 ELONGATION AND CONTRACTION TEST

Two (2) hose assemblies of each size shall be subjected to the elongation and contraction test. The hose shall not change in length by more than +0.20 inch (5.1 mm) in 10 inches (254 mm) of length when subjected to the operating pressure shown in Table I for not less than five (5) minutes. With the hose held in a straight position, unpressurized, a 10-inch (254 mm) gage length shall be marked off on the hose and the hose then pressurized. After five (5) minutes, while still pressurized, the gage length shall be measured and the change in length calculated.

#### 4.6.5 VOLUMETRIC EXPANSION TEST

Two (2) assemblies of each size shall be tested in accordance with ASTM D571. The volumetric expansion of the test assemblies shall be in accordance with the values shown in Table I. This test shall be performed at operating pressure.

#### 4.6.6 LEAKAGE TEST

Two (2) assemblies of each size shall be pressurized to 70 percent of the minimum room temperature burst pressure shown in Table I and held for five (5) minutes minimum. The pressure shall then be reduced to zero (0) psi, after which it shall again be raised to 70 percent of the minimum room temperature burst pressure for a final five (5) minute check. Any evidence of leakage from hose or fitting, hose burst, fitting blow-off or any other evidence of malfunction shall constitute failure.

#### 4.6.7 ROOM TEMPERATURE BURST PRESSURE TEST

Two (2) hose assemblies of each size shall be subjected to a pressure sufficient to burst the assemblies with a rate of pressure rise equal to 20,000 psi  $\pm$  5,000 psi (137 895 kPa  $\pm$  34 474 kPa) per minute. The assemblies shall be observed throughout the test and the type of failure and the pressure where failure occurred shall be recorded. The assemblies shall not leak or show any evidence of malfunction at any pressure below the specified pressure listed in Table I.

#### 4.6.8 THERMAL SHOCK TEST

The thermal shock test shall be as follows:

- a. Two (2) hose assemblies of each size shall be subjected to this test. One (1) assembly shall be air aged and one (1) assembly shall be unaged. The assemblies shall be subjected to the proof pressure specified in Table I for a minimum of five (5) minutes.
- b. The test assemblies shall then be mounted, empty, in a low and high temperature test fixture (typical setup shown in Figure 1). The ambient temperature shall be reduced to  $-65^{\circ}\text{F} \pm 2^{\circ}\text{F}$  ( $-54^{\circ}\text{C} \pm 1^{\circ}\text{C}$ ) for a minimum of two (2) hours. At the end of this period, while still at this temperature, high temperature test fluid at a temperature of  $400^{\circ}\text{F}$  ( $204^{\circ}\text{C}$ ) shall be suddenly introduced at a minimum pressure of 50 psi (345 kPa). Immediately after the hot oil has filled the assembly, the pressure shall be raised to the proof pressure specified in Table I for a minimum of five (5) minutes. Not more than 15 seconds shall elapse between the introduction of the high temperature oil at 50 psi (345 kPa) and the raising of the pressure to proof pressure.
- c. The test assemblies shall then be filled with one of the specified high temperature test fluids at a pressure of 75 psi  $\pm$  25 psi (517  $\pm$  172 kPa) and soaked with ambient, and fluid temperature maintained at  $400^{\circ}\text{F}$  ( $204^{\circ}\text{C}$ ) for one (1) hour. At the end of this period, the assemblies shall be pressurized to the proof pressure specified in Table I for a minimum of five (5) minutes. The pressure shall then be released; and while still maintaining the  $400^{\circ}\text{F}$  ( $204^{\circ}\text{C}$ ), the pressure shall then be increased at the same rate of rise as specified in 4.6.7 until failure is obtained. The hose assemblies shall be under continuous observation during the preceding test, and the pressure where the failure occurred and the type of failure shall be recorded.

## 4.6.8 (Cont'd)

- d. During part b. and the proof portion of part c. of the test, any evidence of leakage from the hose or fittings, hose burst, fitting blow-off or any other evidence of malfunction, shall constitute failure. During the burst portion of part c., any of the above occurring below the minimum high-temperature burst pressure shown in Table I shall constitute failure

## 4.6.9

IMPULSE TEST

Impulse testing shall be performed as follows on six (6) straight-to-90° elbow hose assemblies of each size. The impulse test equipment shall conform to ARP 603 and AIR 1228.

- a. Two (2) assemblies shall be oil aged, two (2) shall be air aged and two (2) shall be unaged. The assemblies shall then be subjected at room temperature to the proof pressure specified in Table I for a minimum of five (5) minutes.
- b. The hose assemblies shall then be pressurized to 3000 psi (20 684 kPa) and while maintaining this pressure at room temperature, the hose assemblies shall be immersed in a  $3.5 \pm 0.1$  percent NaCl solution by weight for 8 to 10 minutes, then allowed to air dry for the remainder of one (1) hour. This sequence of immersion and air drying shall be repeated no less than fifty (50) times. (See Note a)
- c. The test assemblies shall be connected to rigid supports and bent in a U-shape with a bend radius at the apex of the bend as specified in Table I.
- d. The impulse pattern shall be as specified in ARP603, with peak pressures of 150 percent measured at the inlet manifold. Impulsing shall occur at a rate of 70  $\pm$  10 cycles per minute. The test fluid shall be one of the high-temperature test fluids. Fluid temperature shall be maintained at 400°F (204°C) and measured at the test manifold. Ambient temperature shall be 400°F (204°C) and shall be measured at a point within six (6) inches from the hose assemblies.
- e. Impulse testing shall be run in such a manner that the assemblies are temperature-cycled from room temperature to specified fluid and ambient air temperatures a minimum of two (2) times, with a minimum of eighty percent (80%) of the impulse cycles at 400°F (204°C). Any evidence of leakage from the hose or fittings prior to the completion of 250,000 impulse cycles shall constitute failure. (See Note b)

Notes:  $\phi$  a) The sodium chloride (NaCl) shall contain on a dry basis not more than 0.1 percent sodium iodine and not more than 0.5 percent total impurities.

b) It is preferred that testing be continuous with a minimum number of shutdowns to accommodate shift schedules and maintenance.

## 4.6.10

ASSEMBLY FLEXURE TEST

Two (2) hose assemblies of each size shall be mounted in the assembly flexure test setup as illustrated on Figure 2 and subjected to the following test sequence. The assemblies shall be filled with oil as specified in 4.5.3. Temperature indicated is both fluid and ambient. Flexing shall occur at a rate of 70  $\pm$  10 cpm during portions c., d., and e.

- a. The test assemblies shall be soaked with no pressure or flexing at a temperature of  $-67^{\circ}\text{F} \pm 2^{\circ}\text{F}$  ( $-55^{\circ}\text{C} \pm 1^{\circ}\text{C}$ ) for a minimum of one (1) hour.
- b. With no flexing, the test assemblies shall be pressurized to the proof pressure as specified in Table I with the temperature still at  $-67^{\circ}\text{F}$  ( $-55^{\circ}\text{C}$ ) for a minimum of five (5) minutes (first cycle only).
- c. Flexing shall begin while the test assemblies are pressurized to the operating pressure as specified in Table I with the temperature still at  $-67^{\circ}\text{F}$  ( $-55^{\circ}\text{C}$ ) for a minimum of 4,000 flexure cycles.
- d. With the pressure reduced to zero (0) psi, flexing shall continue for 1,000 flexure cycles at  $-67^{\circ}\text{F}$  ( $-55^{\circ}\text{C}$ ).
- e. Increase the temperature to 400°F (204°C) for hose sizes through -16 and to 275°F (135°C) for hose size -20 and flex for 1,000 cycles with pressure at zero (0) psi. The pressure shall then be increased to the operating pressure specified in Table I with the temperature held at 400°F (204°C). Flexing shall continue until an accumulated total of 80,000 cycles is reached.
- f. Steps a., c., d., and e. shall be repeated for a total of five (5) test sequences (i.e., 400,000 flexing cycles).

- g. After completion of step f., and with no flexing, the test assemblies shall be pressurized to the proof pressure specified in Table I with the temperature still at 400°F (204°C) for hose sizes through -16 and to 275°F (135°C) for hose size -20 for a minimum of five (5) minutes (last cycle only).

Any leakage from the hose or fittings, hose burst, fitting blow-off, or any other evidence of malfunction during the test, shall constitute failure.

## 4.6.11

STRESS DEGRADATION TEST

Two (2) hose assemblies of each size shall be subjected to the following test sequence:

- a. The hose assemblies shall be filled with one of the specified high-temperature test fluid and placed in an oven which shall be maintained at a temperature of 400°F (204°C). Precautions shall be taken to ensure that the hose assemblies do not come in contact with part of the oven that are at higher temperatures. A pressure equal to the operating pressure specified in Table I shall be applied to the hose assemblies.
- b. After a minimum of 20 hours at 400°F (204°C), the pressure shall be gradually released and the assemblies removed from the oven, drained, and cooled to room temperature.
- c. The hose assemblies shall then be filled with fluid conforming to MIL-H-5606. A pressure equal to the operating pressure specified in Table I shall be applied and held for a minimum of two (2) hours at room temperature.
- d. The procedure specified in steps a., b., and c. shall be repeated a total of three (3) times.
- e. After the final two (2) hour pressurization period, the hose assemblies shall be drained and flushed with trichloroethylene, conforming to MIL-T-27602, and placed in an oven for one (1) hour. The temperature of the oven shall be maintained at 160°F  $\pm$  10°F (71°C  $\pm$  5°C).
- f. The hose assemblies shall be removed from the oven, cooled to room temperature, and then subjected to an air under water test. To conduct this test, the hose assemblies shall be installed in an apparatus constructed similar to that shown in Figure 3.
- g. The apparatus with the hose assembly installed, shall be immersed in water containing no wetting agent. A pressure equivalent to the operating pressure specified in Table I shall be applied for 15 minutes to allow any entrapped air in the hose to escape.
- h. The pressure shall be held an additional five (5) minute period, during which time the effused gas shall be collected from the test sample, including the juncture of the hose and the fitting, but not including the "B" nut. After the five (5) minute period of pressurization, the average rate of effusion through the hose and two (2) fittings shall be computed into cc/in./min.). If the average rate of effusion exceeds 2.0 cc/in./min. (0.78 cc/cm/min.) for any size, it shall be cause for rejection and considered failure to qualify.

## 4.6.12

PNEUMATIC SURGE TEST

Two (2) hose assemblies that were subjected to the stress degradation (4.6.11) shall be used for this test. The hose assemblies shall be installed in the test apparatus in accordance with Figure 4. The assemblies shall be tested using compressed gas to the rated operating pressure specified in Table I, for 25 minutes at room temperature. After this period of pressurization, the exhaust valve shall be opened within 50 milliseconds to permit rapid discharge of the compressed gas. After (5) minutes, the valve shall be closed and the pressure recycled. This sequence of 25 minutes at operating pressure and 5 minutes at zero (0) psi shall be repeated a total of 16 times. At the end of this period, the hose shall be sectioned and examined for evidence of tube collapse, sponging of the inner tube, etc., and the filter downstream of the hose examined for evidence of inner tube particles. Any evidence of hose degradation, as noted, shall constitute failure.

## 4.6.13

PNEUMATIC EFFUSION TEST

Two (2) hose assemblies of each size shall be used for this test. The assemblies shall be subjected to the operating pressure specified in Table I for one (1) hour at room temperature. Air effusion shall be collected, using the water displacement method and an air collecting device similar to that depicted in Figure 3. The total amount of effusion through the hose and the two (2) fittings shall be collected over the last 1/2 hour of testing. Total effusion shall not exceed 8.0 cc/ft. (26 cc/m) of hose assembly for any size hose.

4.6.14 OVERTIGHTENING TORQUE TEST

Two (2) hose assemblies of each size shall be subjected to the test procedure and recommended torque values in accordance with ARP 908.

4.6.15 CONDUCTIVITY TEST

One (1) test specimen in accordance with Figure 5 shall be subjected to the conductivity test as follows:

- a. The test specimen shall be a length of hose (with braid and one end fitting) as shown in Figure 5. The inner surface of the tube shall be washed first with solvent conforming to P-D-680, and then with isopropyl alcohol conforming to TT-I-735, to remove surface contamination, and thoroughly dried at room temperature. The wire braid shall flare out as shown in Figure 5 to prevent contact with the end of the tetrafluoroethylene tube. One MS21900 steel adapter of appropriate size shall be assembled to the hose end fitting as shown on Figure 5.
- b. The test specimen shall then be arranged vertically as shown on Figure 5. The relative humidity shall be kept below 70 percent and room temperature between 60°F (16°C) and 90°F (32°C). One thousand (1000) volts dc shall be applied between the upper mercury electrode and the lower (MS21900 adapter) electrode.
- c. The current shall be measured with an instrument with a sensitivity of at least one (1) microampere ( $1 \times 10^{-6}$  ampere). The current measured shall be equal to or greater than, six (6) microamperes for sizes -4 through -8 and equal to or greater than, twelve (12) microamperes for sizes -10 through -16.

5. PREPARATION FOR DELIVERY5.1 PRESERVATION AND PACKAGING

Preservation and packaging shall be level A or C, as specified (see 6.2).

5.1.1 LEVEL A

Hose assemblies shall be preserved in accordance with method III of MIL-P-116. All openings shall be sealed with caps or plugs conforming to MIL-C-5501. Hose assemblies shall be unit packaged in containers conforming to PPP-B-566, PPP-B-636, PPP-B-665, or PPP-B-676. The gross weight of the boxes shall not exceed the weight limitations of the applicable container specification.

5.1.2 LEVEL C

Hose assemblies shall be preserved and packaged in accordance with the manufacturer's commercial practice.

5.2 PACKING

Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 LEVEL A

Hose assemblies preserved and packaged to meet 5.1.1 shall be packed in exterior type shipping containers conforming to PPP-B-585, PPP-B-591, PPP-B-601, PPP-B-636 or PPP-B-756. Insofar as practical, exterior containers shall be of uniform shape and size, of minimum cube and tare consistent with the protection required, and shall contain identical quantities. The gross weight of each pack shall be limited to approximately 200 pounds (90 kg.). Containers shall be closed and strapped in accordance with the applicable specification or appendix thereto. Containers shall be provided with a case liner conforming to MIL-L-10547 and shall be sealed in accordance with the appendix thereto. The case liner will not be required when the unit, intermediate, or exterior container conforms to PPP-B-636 and is sealed at all joints and seams, including manufacturer's joint, with tape conforming to PPP-T-60.